

**REMARKS**

**I. Claim Amendments**

Claims 1-4 are canceled.

Claims 5 and 7 are amended to clarify that the claims are directed to an image forming system comprising an image-forming apparatus and a toner. No new matter has been added.

After entry of this amendment, claims 5-8 will be pending in the application.

**II. Response to Objections to the Disclosure**

At pages 3 and 4 of the Office Action, the disclosure is objected to because not all of the trademarks were capitalized and spelled correctly in the substitute specification filed on September 28, 2005.

In response, Applicants have amended the disclosure by correcting the trademarks in the Substitute Specification provided herewith. No new matter has been added.

Accordingly, Applicants respectfully request reconsideration and withdrawal of this objection.

**III. Response to Claim Rejections Under 35 U.S.C. § 112, Second Paragraph**

At page 5, paragraph 6 of the Office Action, claims 5-8 are rejected under 35 U.S.C. § 112, second paragraph, as allegedly being indefinite.

Specifically, the Examiner contends that claims 5 and 7 are indefinite in the phrase “[a]n image-forming apparatus comprising ... a toner,” because the structural relationship between the apparatus and the toner is not clear. The Examiner further states that the toner is merely a material that is worked upon by the apparatus, rather than a structural element of the apparatus.

In response, Applicants have amended claims 5 and 7 to clarify that the claims are directed to an “image forming system” comprising both the apparatus and the toner.

Applicants submit that claims 5-8 particularly point out and distinctly claim the subject matter which Applicants regard as the invention, and thus respectfully request reconsideration and withdrawal of this rejection.

#### **IV. Response to Objections to the Claims**

At page 5, paragraph 7 of the Office Action, claim 7 is objected to because the term “ $G(t=0.01)[Pa]$ ” is missing a closing bracket.

Applicants have amended claim 7 by adding the closing bracket, and thus respectfully request reconsideration and withdrawal of this objection.

#### **V. Response to Claim Rejections Under 35 U.S.C. §§ 102(b) and 103(a)**

At pages 6-9 of the Office Action, claims 1 and 3 are rejected under 35 U.S.C. § 102(b) as allegedly anticipated by or, in the alternative, under 35 U.S.C. 103(a) as allegedly obvious over WO 02/084408 A1 (Matsumura).

Claims 1 and 3 have been canceled, rendering this rejection moot.

**VI. Response to Claim Rejections Under 35 U.S.C. § 102(e)**

At pages 10 and 11 of the Office Action, claims 1-4 are rejected under 35 U.S.C. § 102(e) as allegedly being anticipated by U.S. 2005/0100807 A1 (Yamazaki), as allegedly evidenced by Applicants' admissions I.

Claims 1-4 have been canceled, rendering this rejection moot.

**VII. Response to Double Patenting Rejection**

At pages 12-16 of the Office Action, claims 1-4 are provisionally rejected under the judicially created doctrine of obviousness-type double patenting as allegedly being unpatentable over claims 1 and 2 of copending U.S. Pat. Appln. No. 10/787,394.

Claims 1-4 have been canceled, rendering this rejection moot.

**VIII. Conclusion**


In view of the above, reconsideration and allowance of this application are now believed to be in order, and such actions are hereby solicited. If any points remain in issue which the Examiner feels may be best resolved through a personal or telephone interview, the Examiner is kindly requested to contact the undersigned at the telephone number listed below.

AMENDMENT UNDER 37 C.F.R. § 1.116  
U.S. Appln. No.: 10/787,389

Atty. Docket No. Q80155

The USPTO is directed and authorized to charge all required fees, except for the Issue Fee and the Publication Fee, to Deposit Account No. 19-4880. Please also credit any overpayments to said Deposit Account.

Respectfully submitted,

A handwritten signature in black ink, appearing to read "Lisa E. Stahl", written over a horizontal line.

Lisa E. Stahl  
Registration No. 56,704

SUGHRUE MION, PLLC  
Telephone: (202) 293-7060  
Facsimile: (202) 293-7860

WASHINGTON OFFICE

**23373**

CUSTOMER NUMBER

Date: March 15, 2006



**PATENT APPLICATION**

**IN THE UNITED STATES PATENT AND TRADEMARK OFFICE**

In re application of

Docket No: Q80155

Rie MIYAZAKI , et al.

Appln. No.: 10/787,389

Group Art Unit: 1756

Confirmation No.: 4816

Examiner: Janis L. Dote

Filed: February 27, 2004

For: TONER

**SUBSTITUTE SPECIFICATION - WITH MARKING  
(123 PAGES)**

Date Filed: March 15, 2006



## TONER

### FIELD OF THE INVENTION

5           The present invention relates to a technical field of a toner used for fixing by heating images of electrostatic images in electrophotography, electrostatic recording and electrostatic printing.

10

### BACKGROUND OF THE INVENTION

As electrophotography, a method of forming an electrostatic charge image on a photosensitive material, developing the electrostatic charge image by a toner which  
15 is carried on a developing roller, transferring the toner image developed on the photosensitive material directly to a recording medium, e.g., paper, or via an intermediate transfer substance, and fixing the toner image on the recording medium by a fixing roller, e.g., a heating roller,  
20 on the recording medium, e.g., paper, by press-heating is known.

For obtaining high quality images, the toners used in such a fixing unit by heating fixation are required to have excellent fixing characteristics that a recording  
25 medium surely separates from fixing members and does not

wind round fixing members after heating fixation at the exit of a fixing unit, and toners do not bring about a so-called hot offset, i.e., the adhesion of melted toners on a heating roller.

5           In fixation using a heating roller, as the factors which control the fixing property and offset resistance of a toner, it is well known that the storage modulus  $G'$  and the loss modulus  $G''$  in dynamic viscoelastic characteristics of a toner have influence. Storage modulus  $G'$  and loss  
10 modulus  $G''$  are viscoelastic characteristics of a substance having general viscoelasticity defined by complex elastic modulus in vibration experiment, and the real number part of complex elastic modulus is called storage modulus  $G'$  and the imaginary number part is called loss modulus  $G''$ ,  
15 specifically, storage modulus is made an index showing the degree of the elasticity of a toner and loss modulus is made an index showing the degree of viscosity.

          In general, toners containing a binder resin comprising a polymer show a stress relaxation behavior that  
20 generated stress exponentially attenuates when constant strain is given. Therefore, for the purpose of the improvement of fixing property of toner images, such as offset of toners to a fixing roller, and the fixing strength of toners on a recording medium, e.g., paper, and  
25 the improvement of dispersibility of colorants, the

relaxation modulus and relaxation time of toners which can be obtained by measuring the dynamic viscoelasticity have been conventionally used for confirming the characteristics of toners quantitatively.

5           Since such a stress relaxation behavior of a toner is greatly influenced by the viscoelasticity of a binder resin and the structure, size and quantity of a release agent dispersed in the resin, the molten condition of a toner can be expressed with a stress relaxation behavior,  
10 i.e., relaxation modulus  $G(t)$  and relaxation time. It is proposed, therefore, to improve the stability of a toner image, the dispersibility of a release agent, and OHP transparency by the expressing molten condition of a toner at fixing time with relaxation modulus  $G$  of viscoelastic  
15 characteristics and relaxation time.

That is, in the toner in this proposal, it is proposed to improve the separability of a fixed sheet, the adhesion property of a fixed image, the bending resistance of a fixed image, the dispersibility of the release agent  
20 in a toner, the dispersibility of the colorant in a toner, and fixing characteristics, such as OHP transparency, by prescribing the initial relaxation modulus  $G(t=0.01)$  in relaxation time of 0.01 sec obtained by the measurement of the dynamic viscoelastic characteristics of the binder  
25 resin of a toner within a prescribed range, and,



considering the heating time  $Dt$  in fixation, by prescribing the ratio  $G(r)$  of the initial relaxation modulus  $G(t=0.01)$  to the initial relaxation modulus  $G(t=0.1)$  in relaxation time of 0.1 sec,  $[G(t=0.01)/G(t=0.1)]$ , within  
5 a prescribed range. (Refer to, e.g., patent literature 1).

On the other hand, the configurations of the fixing nip parts of fixing members used in fixing units by heating fixation are various.

For instance, fixing units having a fixing nip part  
10 of a heating roller and a pressing roller of fixing members taking the configuration of protruding toward the pressing roller side are known (refer to, e.g., patent literature 2).

[Patent literature 1]

15 Japanese Patent No. 3241003 (paragraphs [0020], [0030], [0031] and [0051]).

[Patent literature 2]

JP-A-2002-268430 (paragraphs [0014], [0015] and Fig.  
3) (the term "JP-A" as used herein refers to an "unexamined  
20 published Japanese patent application).

Various different nip configurations have a great influence on the direction of discharge of a recording medium when discharged from a fixing unit.

25 For example, in the fixing unit disclosed in patent

literature 2, since the fixing nip part of the heating roller and the pressing roller takes the configuration of protruding toward the pressing roller side, the direction of discharge of a recording medium tends to be the  
5 direction along the heating roller. Due to this tendency, the recording medium is liable to wind round the heating roller after heating fixation.

However, in the toner disclosed in patent literature 1, it is disclosed to improve fixing characteristics, such  
10 as fixing strength, of a toner image by expressing the molten state of a toner by the ratio  $G(r)$  of the relaxation modulus  $G(t)$ , where heating time  $Dt$  at fixing time is considered, and the relaxation modulus  $G(t)$  after the elapse of certain relaxation time. However, the nip  
15 configuration of the fixing unit is not supposed at all in the same patent. Therefore, there remains a problem that it is difficult to effectively prevent a recording medium from winding round the heating roller.

Further, when a toner is made soft for the purpose  
20 of improving fixing strength and the like, not only the winding of a recording medium round a heating roller is liable to occur, but hot offset is also liable to occur by the reluctance of separation of softened toner.

## SUMMARY OF THE INVENTION

The present invention has been done in view of these circumstances, and an object of the present invention is to provide a toner capable of effectively repressing hot  
5 offset of a toner in fixing characteristics, while effectively preventing the winding of a recording medium round a fixing member.

In a first aspect of the present invention (hereinafter referred to as "first invention"), the first  
10 invention mainly relates to following items:

(1) A toner for use in an image-forming apparatus equipped with an oil-less fixing unit comprising a main heating member and a pressing member, the main heating member gets in contact with the back of an unfixed toner on  
15 a recording medium and fixes the unfixed toner at a nip part of the main heating member and the pressing member, the main heating member and the pressing member define a boundary surface thereof, and the surface takes a configuration protruding toward the side of the main  
20 heating member,

wherein the toner has a initial relaxation modulus  $G$  ( $t=0.01$ ) (Pa) at  $120^{\circ}\text{C}$ , in relaxation time of 0.01 (sec), of  $G$  ( $t=0.01$ ) [Pa]  $\geq 1.0 \times 10^5$  [Pa],

wherein the toner has a ratio of  $G$  ( $t=0.01$ ) (Pa) to  
25  $G$  ( $t=0.1$ ) (Pa) at  $180^{\circ}\text{C}$ , in relaxation time of 0.1 sec, of

$[G(t=0.01)/G(t=0.1)] \geq 20.$

(2) The toner according to item 1, wherein the toner contains a release agent in an amount of 3 wt.% or less.

5 In a second aspect of the present invention (hereinafter referred to as "second invention"), the first invention mainly relates to following items:

(3) A toner for use in an image-forming apparatus equipped with an oil-less fixing unit comprising a main  
10 heating member and a pressing member, the main heating member gets in contact with the back of an unfixed toner on a recording medium and fixes the unfixed toner at a nip part of the main heating member and the pressing member, the main heating member and the pressing member define a  
15 boundary surface thereof, and the surface takes a configuration protruding toward the side of the main pressing member,

wherein the toner has a initial relaxation modulus  $G(t=0.01)$  (Pa) at 120°C, in relaxation time of 0.01 (sec),  
20 of  $G(t=0.01)$  [Pa]  $\geq 1.0 \times 10^5$  [Pa],

wherein the toner has a initial relaxation modulus  $G(t=0.01)$  (Pa) at 180°C, in relaxation time of 0.01 (sec),  
of  $G(t=0.01)$  [Pa]  $\geq 1.0 \times 10^4$  [Pa].

(4) The toner according to item 3, wherein the  
25 toner contains a release agent in an amount of 3 wt.% or

less.

A viscoelasticity regulated in the present invention can be provided by regulating molecular weight, molecular weight distribution, degree of cross-linkage and molecular  
5 structure of a resin in the toner of the present invention.

#### BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a drawing typically showing an example of  
10 a fixing unit to which the toner of the first invention is applied; (a) is a front view, and (b) is an enlarged view of part IB in Fig. (a).

Fig. 2 is a drawing typically showing an example of a fixing unit to which the toner of the second invention is  
15 applied; (a) is a front view, and (b) is an enlarged view of part IB in Fig. (a).

Fig. 3 is a drawing showing an example of relaxation modulus  $G$  of a toner comprising a binder resin of a general polymer.

20 Fig. 1 is a drawing typically showing a measuring instrument of viscoelasticity of a toner.

#### DETAILED DESCRIPTION OF THE INVENTION

25 Fig. 1 is a drawing typically showing an example of

a fixing unit to which the toner of the first invention is applied; (a) is a front view, and (b) is the enlarged view of part IB in Fig. (a).

The fixing unit shown in Fig. 1 is a fixing which  
5 can be used in the first invention as an oil-less fixing unit, wherein the toner is fixed by heating from the backside of the fixing toner surface. In the figure, 110 is a heating roller (a heating member), 111 is a metal pipe, 112 is a heat transfer elastic body provided on the outer  
10 periphery of pipe 111, 113 is a heater inserted into the inside of pipe 111, 114 is a high heat transfer member in contact with the inner periphery of pipe 111, 120 is a pressing roller (a pressing member), 121 is a shaft, 122 is a pressing member charged around shaft 121, P is a paper (a  
15 recording medium), T is the toner of the toner image on paper P, and N is a fixing nip part where rollers 110 and 120 are in contact with each other with pressure. The fixing unit of this example is equipped with one heating roller 110, accordingly heating roller 110 corresponds to  
20 the main heating member of the first invention. Since the structure of heat transfer from heater 113 and high heat transfer member 114 to pipe 111 is substantially the same as the heating roller disclosed in JP-A-2002-268430, and is easily understood by referring to the same patent, the  
25 details are omitted here.

Rollers 110 and 120 of this fixing unit are in contact with each other with pressure. In that case, as shown in Fig. 1 (b) by enlargement, elastic body 112 of heating roller 110 is concaved elastically by pressing member 122 of pressing roller 120. Thus fixing nip part N in this fixing unit takes the configuration of convexity toward main heating member heating roller 110 side in the orthogonal section of both rotary shafts of heating roller 110 and pressing roller 120 (configuration of protruding downward in Fig. (a) and (b)). In the case of a fixing unit not using a heating roller and a pressing roller, the section that defines the convexity is substantially the same section as the orthogonal section of both rotary shafts.

In the fixing unit shown in the figure, when heating roller 110 is rotated clockwise, pressing roller 120 rotates anticlockwise by the rotation of heating roller 110. In the state of rotating both rollers 110 and 120, paper P on which a toner image has been transferred by a transfer member not shown in the figure is heated by heater 113 of heating roller 110 from the backside of the toner fixing surface via paper P while transiting through fixing nip part N of heating roller 110 and pressing roller 120 in the direction shown by the arrow (on the right side in the figure), thereby the toner image is fixed on paper P. At

this time, uniformization of temperature distribution in the direction of shaft line of heating roller 110 is efficiently contrived with high heat transfer member 114.

In the fixing unit shown in Fig. 1 (a) and (b),  
5 heating roller 110 is provided only on the backside of the toner image side (fixing surface side) of paper P and heats paper P from the backside, but a fixing unit in which the toner of the first invention is used may be equipped with a heater also on the toner image side (fixing surface side)  
10 of paper P in addition to heater 113 to thereby heat paper P secondarily from the fixing surface side. In such a case, heating roller 110 directly in contact with the backside of paper P is a main heating member.

In the exemplified fixing unit, two rollers of  
15 heating roller 110 and pressing roller 120 are used as fixing members but a fixing unit equipped with a belt and rollers can also be used.

A binder resin capable of controlling dynamic viscoelastic characteristics in fixing region is used in  
20 the toner of the first invention. In stress relaxation measurement described later, this binder resin of the toner has initial relaxation modulus  $G(t=0.01)$  (Pa) in relaxation time of 0.01 (sec), which is the starting time of measuring stress relaxation, at 120°C of  $1.0 \times 10^5$  [Pa] or  
25 more {initial relaxation modulus  $G(t=0.01)$  [Pa]  $\geq 1.0 \times 10^5$



[Pa], and preferably  $G(t=0.01)$  [Pa]  $\geq 1.2 \times 10^5$  [Pa] }.

Here, relaxation time 0.01 (sec) is the time required to be capable of measuring stress relaxation after applying stress on a toner and restoring a stationary state in stress relaxation measurement described later, i.e., the starting time of the measurement of stress relaxation.

Further, the toner of the first invention has the ratio of the initial relaxation modulus  $G(t=0.01)$  (Pa) to the relaxation modulus  $G(t=0.1)$  (Pa) in relaxation time of 0.1 sec  $[G(t=0.01)/G(t=0.1)]$  at 180°C of  $[G(t=0.01)/G(t=0.1)] \geq 20$ , and preferably  $[G(t=0.01)/G(t=0.1)] \geq 25$ .

Here, the ratio  $[G(t=0.01)/G(t=0.1)]$  represents the rate of variation (relaxation velocity) of relaxation modulus  $G(t)$  after the elapse from relaxation time 0.01 (sec) to relaxation time 0.1 (sec).

Fig. 2 is a drawing typically showing an example of a fixing unit to which the toner of the second invention is applied; (a) is a front view, and (b) is the enlarged view of part IB in Fig. (a).

The fixing unit shown in Fig. 2 is a fixing which can be used in the second invention as an oil-less fixing unit, wherein the toner is fixed by heating from the backside of the fixing toner surface. In the figure, 210 is a heating roller (a heating member), 211 is a metal pipe, 212 is a heater inserted into the inside of pipe 211, 213

is an inner periphery of pipe 211, 214 is a high heat transfer member in contact with the inner periphery 213 of pipe 211, 220 is a pressing roller (a pressing member), 221 is a shaft, 222 is an elastic body charged around shaft 221, 5 P is a paper (a recording medium), T is the toner of the toner image on paper P, and N is a fixing nip part where rollers 210 and 220 are in contact with each other with pressure. The fixing unit of this example is equipped with one heating roller 210, accordingly heating roller 210 10 corresponds to the main heating member of the second invention.

Since the structure of heat transfer from heater 213 and high heat transfer member 214 to pipe 211 is substantially the same as the heating roller disclosed in 15 JP-A-2002-268430, and is easily understood by referring to the same patent, the details are omitted here.

Rollers 210 and 220 of this fixing unit are in contact with each other with pressure. In that case, as shown in Fig. 2 (b) by enlargement, elastic body 222 of 20 pressing roller 220 is concaved elastically by metal pipe 211 of heating roller 210. Accordingly, fixing nip part N in this fixing unit takes the configuration of convexity toward pressing roller 220 side in the orthogonal section of both rotary shafts of heating roller 210 and pressing 25 roller 220 (configuration of protruding upward in Fig. (a))

and (b)). In the case of a fixing unit not using a heating roller and a pressing roller, the section that defines the convexity is substantially the same section as the orthogonal section of both rotary shafts.

5        In the fixing unit shown in the figure, when heating roller 210 is rotated clockwise, pressing roller 220 rotates anticlockwise by the rotation of heating roller 210. In the state of rotating both rollers 210 and 220, paper P on which a toner image has been transferred by a transfer  
10 member not shown in the figure is heated by heater 212 of heating roller 210 while transiting through fixing nip part N of heating roller 210 and pressing roller 220 in the direction shown by the arrow (on the right side in the figure), thereby the toner image is fixed on paper P. At  
15 this time, uniformization of temperature distribution in the direction of shaft line of heating roller 210 is efficiently contrived with high heat transfer member 214.

      In the fixing unit shown in Fig. 2 (a) and (b), heating roller 210 is provided only on the backside of the  
20 toner image side (fixing surface side) of paper P and heats paper P from the backside, but a fixing unit in which the toner of the second invention is used may be equipped with a heater also on the toner image side (fixing surface side) of paper P in addition to heater 212 to thereby heat paper  
25 P secondarily from the fixing surface side. In such a case,

heating roller 210 directly in contact with the backside of paper P is a main heating member.

In the exemplified fixing unit, two rollers of heating roller 210 and pressing roller 220 are used as  
5 fixing members but a fixing unit equipped with a belt and rollers can also be used.

A binder resin capable of controlling dynamic viscoelastic characteristics in fixing region is used in the toner of the second invention. In stress relaxation  
10 measurement described later, this binder resin of the toner has initial relaxation modulus  $G(t=0.01)$  (Pa) in relaxation time of 0.01 (sec), which is the starting time of measuring stress relaxation, at 120°C of  $1.0 \times 10^5$  [Pa] or more {initial relaxation modulus  $G(t=0.01)$  [Pa]  $\geq 1.0 \times 10^5$   
15 [Pa], and preferably  $G(t=0.01)$  [Pa]  $\geq 1.2 \times 10^5$  [Pa]}.

Here, relaxation time 0.01 (sec) is the time required to be capable of measuring stress relaxation after applying stress on a toner and restoring a stationary state in stress relaxation measurement described later, i.e., the  
20 starting time of the measurement of stress relaxation.

Further, this binder resin of the toner has initial relaxation modulus  $G(t=0.01)$  (Pa) in relaxation time of 0.01 (sec) at 180°C of  $1.0 \times 10^4$  [Pa] or more {initial relaxation modulus  $G(t=0.01)$  [Pa]  $\geq 1.0 \times 10^4$  [Pa], and  
25 preferably  $G(t=0.01)$  [Pa]  $\geq 1.2 \times 10^4$  [Pa]}.

As the binder resins which are used in the toner of the present invention and capable of controlling viscoelastic characteristics in a fixing region, binder resins having both a crystalline region and an amorphous region are preferably used, e.g., resins having a urethane bond and a urea bond, resins comprising the blend of a crystalline polyester resin and an amorphous polyester resin, and polyester resins comprising a block copolymer of a crystalline part and an amorphous part, are exemplified. Amorphous polyester and block polyester are particularly preferably used as the binder resins of the invention.

Viscoelastic characteristics in the fixing region can also be controlled in the compositions which are designed to previously control the polymerization of a binder resin by blending a polymerization initiator and a crosslinking initiator which exhibit their functions when heat energy higher than the prescribed quantity is given at fixing time, thereby the polymerization of the binder resin in the toner progresses when heat energy is given in the range of fixing temperature, and the binder resin is crosslinked and the molecular weight increases.

The binder resin for use in the toner of the present invention comprises a polymer, and a polymer generally has a property of showing viscoelastic characteristics in a molten state of a toner. As is shown in Fig. 3, when

certain strain is given, the stress of the toner is relaxed with time  $t$  (sec) in the stress relaxation measurement described later, so that the relaxation modulus  $G(t)$  [Pa], which is one of viscoelastic characteristics, shows a  
5 property of lessening with relaxation time  $t$  (sec).

As the binder resins in toners having these viscoelastic characteristics, the toner of the invention is described below with binder resins using conventionally well-known polyester resins as an example.

10 The toner of the example comprises toner particles comprising a polyester resin containing a colorant and a charge controlling agent kneaded and pulverized. And the binder resin has functions of retaining colorant particles in toner particles, being softened by the heat and pressure  
15 of fixing rollers in fixation, and adhering the toner particles to a transfer material, e.g., paper. However, when the molecular weight of the binder resin is lowered and the softening temperature is lowered for the purpose of low temperature fixation, the reductions of glass  
20 transition temperature, strength, the retention of colorant, offset resistance, the strength of fixed images, and the storage stability are brought about.

#### Constitutional components of toner

25 The toner of the present invention can be

manufactured with materials containing at least a resin as the main component (hereinafter sometimes referred to as merely "a resin").

Each component of the materials for use in  
5 manufacturing the toner of the invention is described below.

#### 1. Resin (binder resin)

The resins (binder resins) in the present invention mainly comprise polyester resins. The content of polyester  
10 resins in the resins is preferably 50 wt.% or more, and more preferably 80 wt.% or more.

In general, polyester resins consist of an alcohol component (including those having 2 or more hydroxyl groups) and a carboxylic acid component (including divalent  
15 or higher carboxylic acids and derivatives thereof).

As the alcohol components, those having 2 or more hydroxyl groups can be used, such as chain diols, e.g., ethylene glycol, 1,3-propanediol, 1,2-propylene glycol, 1,3-propylene glycol, 1,4-butanediol, diethylene glycol,  
20 1,5-pentanediol, 1,6-hexanediol, dipropylene glycol, triethylene glycol, tetraethylene glycol, 1,2- propanediol, 1,3-butanediol, 2,3-butanediol, neopentyl glycol(2,2-dimethylpropane-1,3-diol), 1,2-hexanediol, 2,5-hexane-diol, 2-methyl-2,4-pentanediol, 3-methyl-1,3-pentanediol, 2-  
25 ethyl-1,3-hexanediol, 2-butyl-2-ethyl-1,3-propanediol, 2,4-

diethyl-1,5-pentanediol, polyethylene glycol, polypropylene glycol, and polytetramethylene glycol, cyclic diols, such as alkylene oxide adducts of bisphenol A, e.g., polyoxypropylene(2.2)-2,2-bis(4-hydroxyphenyl)-propane, 5 polyoxypropylene(3.3)-2,2-bis(4-hydroxy-phenyl)propane, polyoxyethylene(2.0)-2,2-bis(4-hydroxy-phenyl)propane, polyoxypropylene-(2.0)-polyoxy-ethylene(2.0)-2,2-bis(4-hydroxyphenyl)propane, and polyoxypropylene(6)-2,2-bis(4-hydroxyphenyl)propane, 2,2-bis(4-hydroxycyclohexyl)propane, 10 alkylene oxide adducts of 2,2-bis(4-hydroxycyclohexyl)propane, 1,4-cyclohexanediol, 1,4-cyclohexanedimethanol, hydrogenated bisphenol A, and alkylene oxide adducts of hydrogenated bisphenol A, and trivalent or higher polyhydric alcohols, e.g., sorbitol, 15 1,2,3,6-hexanetetrol, 1,4-sorbitan, pentaerythritol, dipentaerythritol, tripentaerythritol, 1,2,4-butanetriol, 1,2,5-pentanetriol, glycerol, 2-methylpropanetriol, 2-methyl-1,2,4-butanetriol, trimethylolethane, trimethylolpropane, and 1,3,5-trihydroxymethylbenzene are 20 exemplified.

The alcohol components mainly comprising aliphatic diols having two hydroxyl groups are particularly used in the present invention. Further, the alcohol components may comprise aliphatic alcohols having three or more hydroxyl 25 groups.



As the aliphatic alcohols having two or more hydroxyl groups, such as chain diols, e.g., ethylene glycol, 1,3-propanediol, 1,2-propylene glycol, 1,3-propylene glycol, 1,4-butanediol, diethylene glycol, 1,5-pentanediol, 1,6-hexanediol, dipropylene glycol, triethylene glycol, tetraethylene glycol, 1,2-propanediol, 1,3-butanediol, 2,3-butanediol, neopentyl glycol(2,2-dimethylpropane-1,3-diol), 1,2-hexanediol, 2,5-hexanediol, 2-methyl-2,4-pentanediol, 3-methyl-1,3-pentanediol, 2-ethyl-1,3-hexanediol, 2-butyl-2-ethyl-1,3-propanediol, 2,4-diethyl-1,5-pentanediol, polyethylene glycol, polypropylene glycol, and polytetramethylene glycol, and cyclic diols, e.g., 2,2-bis(4-hydroxycyclohexyl)propane, alkylene oxide adducts of 2,2-bis(4-hydroxycyclohexyl)-propane, 1,4-cyclohexanediol, 1,4-cyclohexanedimethanol, hydrogenated bisphenol A, and alkylene oxide adducts of hydrogenated bisphenol A are exemplified.

Thus in the present invention, the alcohol component mainly comprises aliphatic diol, preferably 50 mol% or more of aliphatic diol, and more preferably 80 mol% or more of aliphatic diol.

As the carboxylic acid components, e.g., divalent or higher carboxylic acids, and derivatives thereof (e.g., acid anhydrides and lower alkyl esters) can be used, e.g., o-phthalic acid (phthalic acid), terephthalic acid,

isophthalic acid, succinic acid, adipic acid, sebacic acid, azelaic acid, octylsuccinic acid, cyclohexanedicarboxylic acid, fumaric acid, maleic acid, itaconic acid, trimellitic acid pyromellitic acid and derivatives of these acids (e.g.,  
5 anhydrides and lower alkyl esters) are exemplified.

In the present invention, it is particularly preferred that the carboxylic acid component comprise divalent dicarboxylic acid.

The examples of divalent carboxylic acids include  
10 e.g., o-phthalic acid (phthalic acid), terephthalic acid, isophthalic acid, succinic acid, adipic acid, sebacic acid, azelaic acid, octylsuccinic acid, cyclohexanedicarboxylic acid, fumaric acid, maleic acid, itaconic acid, and derivatives of these acids (e.g., anhydrides and lower  
15 alkyl esters).

In the present invention, it is particularly preferred to use polyester resins containing block polyesters and amorphous polyesters as described later. These polyester resins are described in detail below.

20

#### 1-1. Block polyester:

Block polyester comprises a block copolymer having a crystalline block obtained by condensation of an alcohol component and a carboxylic acid component, and an amorphous  
25 block that is lower in crystallinity than the crystalline

block.

#### (1) Crystalline block

As compared with amorphous blocks or amorphous  
5 polyesters, crystalline blocks are high in crystallinity.  
That is, the structure of molecular arrangement of  
crystalline blocks is strong and stable as compared with  
those of amorphous blocks or amorphous polyesters.  
Therefore, crystalline blocks contribute to the elevation  
10 of the strength of a toner as a whole. As a result, the  
toner finally obtained is strong in mechanical stresses and  
excellent in durability and storage stability.

Incidentally, highly crystalline resins generally  
have a so-called sharp melt property as compared with low  
15 crystalline resins. That is, highly crystalline resins  
have a property of exhibiting a sharp figure of endothermic  
peak as compared with low crystalline resins when subjected  
to the measurement of endothermic peak of melting  
temperature by differential scanning calorimetry (DSC).

20 On the other hand, as described above, crystalline  
blocks are high in crystallinity. Thus crystalline blocks  
have a function of imparting a sharp melt property to block  
polyesters. Therefore, the toner finally obtained can  
maintain excellent stability in figure at relatively high  
25 temperature (the temperature near the melting temperature

of the block polyester) at which the amorphous polyester described later is sufficiently softened. Accordingly, when these block polyesters are used, a sufficient fixing ability (fixing strength) can be obtained in a broad  
5 temperature range.

Further, crystals having high hardness and appropriate sizes can be precipitated in a toner by the presence of these crystalline blocks. Due to such crystals, the stability of the figure of a toner becomes excellent,  
10 in particular stable to mechanical stresses. In addition, by the presence of these crystals in a toner, external additives, which are described later, can be surely retained around the surfaces of toner particles (mother particles) (external additives can be effectively prevented  
15 from being buried in mother particles), so that the functions of external additives (functions of imparting e.g., excellent flowability and electrification property) can be sufficiently exhibited.

The constitutional components of crystalline blocks  
20 are described below.

As the alcohol components constituting crystalline blocks, those having two or more hydroxyl groups can be used, preferably diol components having two hydroxyl groups. As such diol components having two hydroxyl groups,  
25 aromatic diols having an aromatic cyclic structure and

aliphatic diols not having an aromatic cyclic structure are exemplified. As the aromatic diols, e.g., bisphenol A and alkylene oxide adducts of bisphenol A (e.g., polyoxypropylene(2.2)-2,2-bis(4-hydroxyphenyl)propane, polyoxypropylene(3.3)-2,2-bis(4-hydroxyphenyl)propane, polyoxyethylene(2.0)-2,2-bis(4-hydroxyphenyl)propane, polyoxypropylene(2.0)-polyoxyethylene(2.0)-2,2-bis(4-hydroxyphenyl)propane, and polyoxypropylene(6)-2,2-bis(4-hydroxyphenyl)propane) are exemplified. As the aliphatic diols, such as chain diols, e.g., ethylene glycol, 1,3-propanediol, 1,2-propylene glycol, 1,3-propylene glycol, 1,4-butanediol, diethylene glycol, 1,5-pentane-diol, 1,6-hexanediol, dipropylene glycol, triethylene glycol, tetraethylene glycol, 1,2-propanediol, 1,3-butanediol, 2,3-butanediol, neopentyl glycol(2,2-dimethylpropane-1,3-diol), 1,2-hexanediol, 2,5-hexane-diol, 2-methyl-2,4-pentanediol, 3-methyl-1,3-pentanediol, 2-ethyl-1,3-hexanediol, 2-butyl-2-ethyl-1,3-propanediol, 2,4-diethyl-1,5-pentanediol, polyethylene glycol, polypropylene glycol, and polytetramethylene glycol, and cyclic diols, e.g., 2,2-bis(4-hydroxycyclohexyl)propane, alkylene oxide adducts of 2,2-bis(4-hydroxycyclohexyl)-propane, 1,4-cyclohexanediol, 1,4-cyclohexanedimethanol, hydrogenated bisphenol A, and alkylene oxide adducts of hydrogenated bisphenol A, are exemplified.

The diol components constituting crystalline blocks are not particularly restricted, but preferably at least a part of the diol components is aliphatic diol, more preferably aliphatic diol having 80 mol% or more of the diol components, and still more preferably aliphatic diol having 90 mol% or more. By this constitution, the crystallinity of block polyesters (crystalline block) can be heightened and the above effects can further be elevated.

The diol components constituting a crystalline block preferably have a straight chain molecular structure having from 3 to 7 carbon atoms, and diol components having hydroxyl groups at both terminals (diol represented by the formula:  $\text{HO}-(\text{C})_2\text{H}_n-\text{OH}$  (provided that  $n$  is from 3 to 7)). Since crystallinity increases and friction coefficient lowers by containing these diol components, the resisting properties against mechanical stresses are improved and excellent durability and storage stability can be obtained. The examples of such diols include, e.g., 1,3-propanediol, 1,4-butanediol, 1,5-pentanediol and 1,6-hexanediol. Of these diols, 1,4-butanediol is preferred. By containing 1,4-butanediol, the above effects become particularly conspicuous.

When 1,4-butanediol is contained as the diol component constituting a crystalline block, it is more preferred that the diol constituting a crystalline block

has 50 mol% or more of 1,4-butanediol, and still more preferred that the diol constituting a crystalline block has 80 mol% or more of 1,4-butanediol. By this constitution, the above effects become further conspicuous.

5       As the carboxylic acid components constituting a crystalline block, divalent or higher carboxylic acids and derivatives thereof (e.g., acid anhydrides and lower alkyl esters) can be used. Of those carboxylic acid components, divalent dicarboxylic acids and derivatives thereof are  
10 preferably used. The examples of dicarboxylic acids include, e.g., o-phthalic acid (phthalic acid), terephthalic acid, isophthalic acid, succinic acid, adipic acid, sebacic acid, azelaic acid, octylsuccinic acid, cyclohexanedicarboxylic acid, fumaric acid, maleic acid,  
15 itaconic acid, and derivatives of these acids (e.g., anhydrides and lower alkyl esters).

      The dicarboxylic acid components constituting a crystalline block are not particularly restricted, but it is preferred that the dicarboxylic acid components at least  
20 partially have a terephthalic acid skeleton, more preferably 50 mol% or more of the dicarboxylic acid components have a terephthalic acid skeleton, and still more preferably 80 mol% or more of the dicarboxylic acid components have a terephthalic acid skeleton. By this  
25 constitution, the toner finally obtained comes to be a

toner well balanced in various characteristics required of the toner.

The content of the crystalline block in block polyester is not particularly restricted, but the content is preferably from 5 to 60 mol%, and more preferably from 10 to 40 mol%. When the content of the crystalline block is less than the lower limit, there is the possibility that the effect by containing the crystalline block cannot be sufficiently exhibited according to the content of the block polyester. On the other hand, when the content of the crystalline block is higher than the upper limit, there is the possibility that the compatibility of block polyester and the amorphous polyester described later lowers, since the content of the amorphous block relatively lowers.

Crystalline block may contain components other than the above alcohol components and carboxylic acid components.

The average molecular weight (weight average molecular weight,  $M_w$ ) of the block polyester containing the crystalline block is not particularly limited, but it is preferably from  $1 \times 10^4$  to  $3 \times 10^5$ , and more preferably from  $1.2 \times 10^4$  to  $1.5 \times 10^5$ . When the average molecular weight,  $M_w$ , is less than the lower limit, there is the possibility that the mechanical strength of the finally-obtained toner lowers and sufficient durability (storage stability) cannot



be obtained. When the average molecular weight  $M_w$  is too small, cohesive failure is liable to occur in the fixing of the toner, and the offset resistance tends to lessen.

While when the average molecular weight  $M_w$  exceeds the  
5 upper limit, intercrystalline crack is liable to occur in the fixing of the toner, and the wettability to a transfer material (a recording medium), e.g., paper, lowers, as a result the quantity of heat required in fixing increases.

The glass transition temperature  $T_g$  of block  
10 polyester is not particularly restricted, but it is preferably from 50 to 75°C, and more preferably from 55 to 70°C. When the glass transition temperature is less than the lower limit, the storage stability (heat resistance) of the toner decreases, and there are cases where fusing  
15 occurs among toner particles according to the use environment. On the other hand, when the glass transition temperature exceeds the upper limit, low temperature fixing ability and transparency decrease. When the glass transition temperature is too high, there is the  
20 possibility that the effect of the thermal treatment of sphere-making as described later cannot be sufficiently exhibited. Glass transition temperature can be measured in accordance with JIS K 7121.

The softening temperature of block polyester  $T_m$  is  
25 not particularly restricted, but it is preferably from 90

to 160°C, and more preferably from 100 to 150°C. When the softening temperature is less than the lower limit, the storage stability of the toner lowers and there is the possibility that sufficient durability cannot be obtained.

5 When the softening temperature is too low, cohesive failure is liable to occur in the fixing of the toner, and the offset resistance tends to lessen. While when the softening temperature exceeds the upper limit, intercrystalline crack is liable to occur in the fixing of

10 the toner, and the wettability to a transfer material (a recording medium), e.g., paper, lowers, as a result the quantity of heat required in fixing increases. The softening temperature  $T_{\frac{1}{2}}$  can be found as the temperature of the point on the flow curve corresponding to  $h/2$  of the

15 flow chart for analysis which can be obtained by measuring by using a flow tester on conditions of a sample amount of 1 g, pit of the die of 1 mm, length of the die of 1 mm, load of 20 kgf, preheating time of 300 seconds, temperature at starting of measurement of 50°C, and velocity of

20 temperature-up of 5°C/min.

The melting temperature  $T_m$  of block polyester (the central value  $T_{mp}$  of the peaks in the measurement of the endothermic peak of melting temperature by differential scanning calorimetry as described later) is not

25 particularly restricted, but it is preferably 190°C or more,

and more preferably from 190 to 230°C. When the melting temperature is less than 190°C, there is the possibility that the effect of improving offset resistance cannot be sufficiently obtained. While when the melting temperature is too high, it is required to increase the temperature of materials in the kneading process as described later. As a result, the ester exchange reaction of resin materials is liable to progress, and there are cases where the design of resin is difficult to be sufficiently reflected in the toner finally obtained. Melting temperature can be obtained, e.g., by the measurement of endothermic peak by differential scanning calorimetry (DSC).

When the toner finally obtained is used in a fixing unit having a fixing roller as described later, it is preferred to satisfy the relationship of  $T_{fix} \leq T_m (B) \leq (T_{fix} + 100)$ , more preferably to satisfy the relationship  $(T_{fix} + 10) \leq T_m (B) \leq (T_{fix} + 70)$ , with the melting temperature of block polyester (the central value  $T_m$  of the peaks in the measurement of the endothermic peak of melting temperature by differential scanning calorimetry as described later) as  $T_m (B)$  [°C], and the standard set surface temperature of the fixing roller as  $T_{fix}$  [°C]. By satisfying the relationship, the adhesion of the toner to the fixing roller of the fixing unit described later can be effectively prevented. Further, since block polyester has

a property of making crystal of a proper size easily as described above, stability and durability can be maintained after fixation of the toner on a recording medium by satisfying the above relationship. Particularly when block  
5 polyester is used in combination with the amorphous polyester described later, the amorphous polyester can be sufficiently softened at fixing time. Accordingly, the fixing ability (fixing strength) of the toner on a recording medium can be satisfactorily elevated and the low  
10 temperature fixing ability of the toner can be excelled. In addition, since block polyester is liable to form crystals having high hardness, the obtained toner is excellent in the stability after fixation.

It is preferred that the melting temperature of block  
15 polyester be higher than the softening temperature of the later-described amorphous polyester. By this constitution, the toner finally obtained is improved in the stability of configuration and shows particularly excellent stability against mechanical stresses. Further, when the melting  
20 temperature of block polyester is higher than the softening temperature of the later-described amorphous polyester, e.g., in the thermal treatment of sphere-making as described later, the amorphous polyester can be thoroughly softened while ensuring the stability of configuration of  
25 the powders for manufacturing the toner in a certain degree

by the block polyester. As a result, the thermal sphere-making treatment can be carried out efficiently, and the degree of circularity of the toner (toner particles) finally obtained can be made relatively high.

5           Incidentally, as described above, as block polyesters contain crystalline blocks having high crystallinity, they have a so-called sharp melt property as compared with relatively low crystalline resins (e.g., the later-described amorphous polyesters and the like).

10           As the index showing crystallinity, e.g., with the central value of the peak as  $T_{mp}$  [°C] and the shoulder peak value as  $T_{ms}$  [°C] in the measurement of endothermic peak of melting temperature by differential scanning calorimetry (DSC), the  $\Delta T$  value represented by  $\Delta T = T_{mp} - T_{ms}$  is  
15 exemplified. The smaller the  $\Delta T$  value, the higher is the crystallinity.

The  $\Delta T$  value of block polyester is preferably 50°C or less, and more preferably 20°C or less. The measuring conditions of  $T_{mp}$  [°C] and  $T_{ms}$  [°C] are not especially  
20 restricted, but the measurement is effected by increasing the temperature of the sample block polyester to 200°C at a temperature-up velocity of 10°C/min, lowering the temperature at a temperature-down velocity of 10°C/min, and again at a temperature-up velocity of 10°C/min.

25           Block polyesters are higher in crystallinity than the

amorphous polyesters described later. Accordingly, the relationship  $\Delta T_A > \Delta T_B$  is satisfied, when the  $\Delta T$  value of amorphous polyester as  $\Delta T_A$  [ $^{\circ}\text{C}$ ] and the  $\Delta T$  value of block polyester as  $\Delta T_B$  [ $^{\circ}\text{C}$ ]. In particular in the present  
5 invention, it is preferred the relationship  $\Delta T_A - \Delta T_B > 10$  be satisfied, and it is more preferred that the relationship  $\Delta T_A - \Delta T_B > 30$  be satisfied. By satisfying the relationship, the above-described effects become further conspicuous. However, when the crystallinity of amorphous  
10 polyester is particularly low, there is the case where at least either  $T_{mp}$  or  $T_{ms}$  is difficult to measure (discrimination is difficult). In such a case,  $\Delta T_A$  is taken as  $\infty$  [ $^{\circ}\text{C}$ ].

The heat of fusion  $E_f$  of block polyester obtained in  
15 the measurement of endothermic peak of melting temperature by differential scanning calorimetry is preferably 5 mJ/mg or more, and more preferably 15 mJ/mg or more. When the heat of fusion  $E_f$  is less than 5 mJ/mg, there is the possibility that the above effects due to having  
20 crystalline block cannot be sufficiently exhibited. However, the heat of fusion does not include the quantity of heat of endothermic peak of glass transition temperature. The measuring conditions of the endothermic peak of the heat of fusion are not especially restricted. The heat of  
25 fusion can be found as the value measured by, e.g.,

increasing the temperature of the sample block polyester to 200°C at a temperature-up velocity of 10°C/min, lowering the temperature at a temperature-down velocity of 10°C/min, and again at a temperature-up velocity of 10°C/min.

5       Block polyesters are preferably linear type polymers (polymers not having a crosslinked structure). Linear type polymers have a small friction coefficient as compared with crosslinked polymers. Due to a small friction coefficient, excellent lubricating property can be obtained and the  
10   transfer efficiency of the toner obtained is further improved.

Block polyesters may have blocks other than the aforementioned crystalline blocks and amorphous blocks.

15   1-2. Amorphous polyester:

Amorphous polyesters are lower in crystallinity than the crystalline blocks as described above.

Amorphous polyester is a component that mainly contributes to the improvement of the dispersibility (e.g.,  
20   dispersibility of colorants, release agents, electrification inhibitors and the like), the pulverizing property of kneaded products in manufacturing a toner, fixing ability of a toner (in particular, low temperature fixing ability), transparency, mechanical characteristics  
25   (e.g., elasticity, mechanical strength and the like),

electrification property, and moisture resistance of each component constituting a toner. In other words, when amorphous polyesters described later are not contained in a toner, there are cases where characteristics required of the toner as enumerated above are difficult to be sufficiently shown.

The constitutional components of amorphous polyester are described below.

As the alcohol components constituting amorphous polyesters, those having two or more hydroxyl groups can be used, preferably diols having two hydroxyl groups. As such diol components having two hydroxyl groups, aromatic diols having an aromatic cyclic structure and aliphatic diols not having an aromatic cyclic structure are exemplified. As the aromatic diols, e.g., bisphenol A and alkylene oxide adducts of bisphenol A are exemplified. As the aliphatic diols, such as chain diols, e.g., ethylene glycol, 1,3-propanediol, 1,2-propylene glycol, 1,3-propylene glycol, 1,4-butanediol, diethylene glycol, 1,5-pentanediol, 1,6-hexanediol, dipropylene glycol, triethylene glycol, tetraethylene glycol, 1,2-propanediol, 1,3-butanediol, 2,3-butanediol, neopentyl glycol(2,2-dimethylpropane-1,3-diol), 1,2-hexanediol, 2,5-hexane-diol, 2-methyl-2,4-pentanediol, 3-methyl-1,3-pentanediol, 2-ethyl-1,3-hexanediol, 2-butyl-2-ethyl-1,3-propanediol, 2,4-diethyl-1,5-pentanediol,



polyethylene glycol, polypropylene glycol, and  
polytetramethylene glycol, and cyclic diols, e.g., 2,2-  
bis(4-hydroxycyclohexyl)propane, alkylene oxide adducts of  
2,2-bis(4-hydroxycyclohexyl)-propane, 1,4-cyclohexanediol,  
5 1,4-cyclohexanedimethanol, hydrogenated bisphenol A, and  
alkylene oxide adducts of hydrogenated bisphenol A, are  
exemplified.

As the carboxylic acid components constituting  
amorphous polyester, divalent or higher carboxylic acids  
10 and derivatives thereof (e.g., acid anhydrides and lower  
alkyl esters) can be used, but divalent dicarboxylic acids  
and derivatives thereof are preferably used. The examples  
of dicarboxylic acids include, e.g., o-phthalic acid  
(phthalic acid), terephthalic acid, isophthalic acid,  
15 succinic acid, adipic acid, sebacic acid, azelaic acid,  
octylsuccinic acid, cyclohexanedicarboxylic acid, fumaric  
acid, maleic acid, itaconic acid, and derivatives of these  
acids (e.g., anhydrides and lower alkyl esters).

The dicarboxylic acid components constituting  
20 amorphous polyester are not particularly restricted, but it  
is preferred that the dicarboxylic acid components at least  
partially have a terephthalic acid skeleton, more  
preferably 80 mol% or more of the dicarboxylic acid  
components have a terephthalic acid skeleton, and still  
25 more preferably 90 mol% or more of the dicarboxylic acid

components have a terephthalic acid skeleton. By this constitution, the toner finally obtained comes to be a toner well balanced in various characteristics required of the toner.

5        It is preferred that 50 mol% or more (more preferably 80 mol% or more) of the monomer components constituting amorphous polyester be the same monomer components constituting amorphous block. That is, amorphous polyester and amorphous block are preferably composed of the same  
10    monomer components. The compatibility of block polyester and amorphous polyester becomes particularly excellent by this constitution. The term "monomer components" used here does not mean the monomers used in the manufacture of block polyester and amorphous polyester, but means monomer  
15    components contained in block polyester and amorphous polyester.

Amorphous polyester may contain components other than the above diol components and dicarboxylic acid components.

The average molecular weight (weight average  
20    molecular weight,  $M_w$ ) of amorphous polyesters is not particularly limited, but it is preferably from  $5 \times 10^3$  to  $4 \times 10^4$ , and more preferably from  $8 \times 10^3$  to  $2.5 \times 10^4$ . When the average molecular weight  $M_w$  is less than the lower limit, there is the possibility that the mechanical strength of  
25    the finally-obtained toner lowers and sufficient durability

(storage stability) cannot be obtained. When the average molecular weight  $M_w$  is too small, cohesive failure is liable to occur in the fixing of the toner, and the offset resistance tends to lessen. While when the average  
5 molecular weight  $M_w$  exceeds the upper limit, intercrystalline crack is liable to occur in the fixing of the toner, and the wettability to a transfer material (a recording medium), e.g., paper, lowers, as a result the quantity of heat required in fixing increases.

10       The glass transition temperature  $T_g$  of amorphous polyester is not particularly restricted, but it is preferably from 50 to 75°C, and more preferably from 55 to 70°C. When the glass transition temperature is less than the lower limit, the storage stability (heat resistance) of  
15 the toner decreases, and there are cases where fusing occurs among toner particles according to the use environment. On the other hand, when the glass transition temperature exceeds the upper limit, low temperature fixing ability and transparency decrease. When the glass  
20 transition temperature is too high, there is the possibility that the effect of the thermal treatment of sphere-making as described later cannot be sufficiently exhibited. Glass transition temperature can be measured in accordance with JIS K 7121.

25       The softening temperature of amorphous polyester  $T_m$

is not particularly restricted, but it is preferably from 90 to 160°C, more preferably from 100 to 150°C, and still more preferably from 100 to 130°C. When the softening temperature is less than the lower limit, the storage stability of the toner lowers and there is the possibility that sufficient durability cannot be obtained. When the softening temperature is too low, cohesive failure is liable to occur in the fixing of the toner, and the offset resistance tends to lessen. While when the softening temperature exceeds the upper limit, intercrystalline crack is liable to occur in the fixing of the toner, and the wettability to a transfer material (a recording medium), e.g., paper, lowers, as a result the quantity of heat required in fixing increases.

15        Taking the softening temperature of amorphous polyester as  $T_{\frac{1}{2}}$  (A) [°C], and the melting temperature of the block polyester as  $T_m$  (B), it is preferred that the relationship  $T_m$  (B) > ( $T_{\frac{1}{2}}$  (A) + 60) be satisfied, and it is more preferred the relationship  $(T_{\frac{1}{2}}$  (A) + 60) <  $T_m$  (B) < ( $T_{\frac{1}{2}}$  (A) + 150) be satisfied. By satisfying the relationship, the amorphous polyester can be thoroughly softened while ensuring the stability of configuration of the toner powder in a certain degree by the block polyester at relatively high temperature. As a result, the viscosity of the toner particles can be made relatively low near the fixing

temperature of the toner and the stress relaxation time of the toner can be prolonged. Further, the thermal sphere-making treatment described later can be carried out efficiently, and the degree of circularity of the toner (toner particles) finally obtained can be further improved by satisfying the above relationship. The toner can exhibit excellent fixing ability in a broad temperature range by satisfying the above relationship.

The softening temperature  $T_{\frac{1}{2}}$  can be found as the temperature of the point on the flow curve corresponding to  $h/2$  of the flow chart for analysis which can be obtained by measuring by using a flow tester on conditions of a sample amount of 1 g, pit of the die of 1 mm, length of the die of 1 mm, load of 20 kgf, preheating time of 300 seconds, temperature at starting of measurement of 50°C, and velocity of temperature-up of 5°C/min.

Amorphous polyesters are preferably linear type polymers (polymers not having a crosslinked structure). Linear type polymers have a small friction coefficient as compared with crosslinked polymers. Due to a small friction coefficient, excellent lubricating property can be obtained and the transfer efficiency of the toner obtained is further improved.

As has been described, when block polyesters and amorphous polyesters are used in combination, the

characteristics of block polyesters as mentioned above and the characteristics of amorphous polyesters can be compatible, by which it becomes possible for the toner finally obtained to possess resistance against mechanical stresses (to have sufficient physical stability) and show satisfactory fixing ability (fixing strength) in a broad temperature range.

The compounding ratio of block polyester and amorphous polyester is preferably from 5/95 to 45/55 by weight, and more preferably from 10/90 to 30/70. When the compounding ratio of block polyester is too low, the synergistic effect as described above cannot be sufficiently shown, and there is the possibility that the offset resistance of the toner cannot be improved sufficiently. On the other hand, when the compounding ratio of amorphous polyester is too low, the synergistic effect as described above cannot be sufficiently shown, and there is the possibility that satisfactory low temperature fixing ability and transparency cannot be obtained. Further, when the compounding ratio of amorphous polyester is too low, there is the case where efficient and uniform pulverization is difficult in the pulverization process in the manufacture of toner.

Resins (binder resins) may contain components other than the aforementioned polyester resins.

As the resin components other than polyester resins (the third resin components), e.g., homopolymers or copolymers containing styrene or a styrene substitution product, e.g., polystyrene, poly- $\alpha$ -methylstyrene, chloropolystyrene, styrene-chlorostyrene copolymers, styrene-propylene copolymers, styrene-butadiene copolymers, styrene-vinyl chloride copolymers, styrene-vinyl acetate copolymers, styrene-maleic acid copolymers, styrene-acrylic ester copolymers, styrene-methacrylic ester copolymers, styrene-acrylic ester-methacrylic ester copolymers, styrene- $\alpha$ -methyl chloroacrylate copolymers, styrene-acrylonitrile-acrylic ester copolymers, and styrene-vinylmethyl ether copolymers, epoxy resins, urethane-modified epoxy resins, silicone-modified epoxy resins, vinyl chloride resins, rosin-modified maleic acid resins, phenyl resins, polyethylene, polypropylene, ionomer resins, polyurethane resins, silicone resins, ketone resins, ethylene-ethyl acrylate copolymers, xylene resins, polyvinyl butyral resins, terpene resins, phenol resins, aliphatic or alicyclic hydrocarbon resins are exemplified. These resins can be used either individually or as a combination of two or more thereof.

The content of these resins in the materials is not especially restricted, but the content is preferably from 50 to 98 wt.%, and more preferably from 85 to 97 wt.%.

When the content of resins is less than the lower limit,  
there is the possibility that the functions of resins (e.g.,  
good fixing ability in a broad temperature range) cannot be  
sufficiently shown. On the other hand, when the content of  
5 resins exceeds the upper limit, the contents of the  
components other than resins, e.g., colorants, relatively  
lower, and it becomes difficult to sufficiently show the  
characteristics of toners, e.g., coloring.

As the colorants, pigments and dyes etc. can be used.  
10 The examples of pigments and dyes include, e.g., carbon  
black, spirit black, lamp black (C.I. No. 77266), magnetite,  
titanium black, chrome yellow, zinc chrome, cadmium yellow,  
mineral fast yellow, navel yellow, Naphthol Yellow S, Hansa  
Yellow G, Permanent Yellow NCG, chrome yellow, benzidine  
15 yellow, quinoline yellow, Tartrazine Lake, chrome orange,  
molybdenum orange, Permanent Orange GTR, Pyrazolone Orange,  
Benzidine Orange G, cadmium red, Permanent Red 4R, Watchung  
Red Calcium Salt, eosine lake, Brilliant Carmine 3B,  
manganese violet, Fast Violet B, Methyl Violet Lake,  
20 Prussian blue, cobalt blue, Alkali Blue Lake, Victoria Blue  
Lake, Fast Sky Blue, Indanthrene Blue BC, ultramarine,  
aniline blue, Phthalocyanine Blue, chalco-oil blue, chrome  
green, chromium oxide, Pigment Green B, Malachite Green  
Lake, Phthalocyanine Green, Final Yellow Green G, Rhodamine  
25 6G, quinacridone, Rose Bengale (C.I. 45432), C.I. Direct



Red, C.I. Direct Red 4, C.I. Acid Red, C.I. Basic Red, C.I. Mordant Red 30, C.I. Pigment Red 48:1, C.I. Pigment Red 57:1, C.I. Pigment Red 122, C.I. Pigment Red 184, C.I. Direct Blue 1, C.I. Direct Blue 2, C.I. Acid Blue 9, C.I. Acid Blue 15, C.I. Basic Blue 3, C.I. Basic Blue 5, C.I. Mordant Blue 7, C.I. Pigment Blue 15:1, C.I. Pigment Blue 15:3, C.I. Pigment Blue 5:1, C.I. Direct Green 6, C.I. Basic Green 4, C.I. Basic Green 6, C.I. Pigment Yellow 17, C.I. Pigment Yellow 93, C.I. Pigment Yellow 97, C.I. Pigment Yellow 12, C.I. Pigment Yellow 180, C.I. Pigment Yellow 162, ~~Nigrosine Dye~~ NIGROSINE DYE (C.I. No. 50415B), metal complex dyes, metal oxides, e.g., silica, aluminum oxide, magnetite, maghemite, various ferrites, cupric oxide, nickel oxide, zinc oxide, zirconium oxide, titanium oxide, and magnesium oxide, and magnetic materials containing magnetic metals, e.g., Fe, Co or Ni. These pigments and dyes can be used alone or in combination of two or more.

The flow softening temperature ( $T_m$ ) of the toner of the invention is from 95 to 150°C, preferably from 100 to 140°C, and more preferably from 110 to 130°C. When the flow softening temperature is lower than 95°C, filming resistance is inferior, and when it is higher than 150°C, low temperature fixing property deteriorates.

The glass transition temperature ( $T_g$ ) of the toner of the invention is from 40 to 70°C, preferably from 45 to

67°C, and more preferably from 50 to 60°C. When the glass transition temperature (T<sub>g</sub>) is lower than 40°C, storage stability lowers, and when it is higher than 70°C, T<sub>m</sub> increases with the increase of T<sub>g</sub> and low temperature fixing property deteriorates.

Since the binder resins in the present invention are great in intermolecular bonding strength and high crystalline polymers, the lowering breadth of T<sub>g</sub> can be lessened when the molecule is designed to lower T<sub>m</sub> by lowering the molecular weight, therefore, low T<sub>m</sub> and low T<sub>g</sub> can be compatible. Further, the melt viscosity at running point of 50% can be made from  $2 \times 10^2$  to  $3 \times 10^4$  Pa·s, thus the toner of the invention is preferred for oil-less fixing.

In the toner of the first invention constituted as above, when a toner image by this toner is fixed by backside heating with, e.g., a fixing unit as shown in Fig. 1 (a) and (b), unfixed toner T of the toner image on paper P is fixed by heating from the backside with a main heating member heating roller 110. Since fixing nip part N takes the configuration protruding toward the side of heating roller 110, paper P is discharged from the outlet of fixing nip part N along by the line of the protruding configuration of nip part N. Therefore, fixed toner T' on the recording medium tries to move along by pressing roller 120. And the temperature of heating-fixed toner T' on

paper P discharged from the fixing nip outlet lowers.

In stress relaxation measurement, initial relaxation modulus  $G(t=0.01)$  (Pa) in relaxation time of 0.01 (sec) of the starting time of measuring stress relaxation at 120°C, the temperature lowered after being discharged from the outlet of fixing nip part N, of the toner of the first invention is: initial relaxation modulus  $G(t=0.01)$  [Pa]  $\geq 1.0 \times 10^5$  [Pa], thus, toner T melted in fixing nip part N is brought to have relatively sufficient elasticity after being discharged from the outlet of fixing nip part N. Accordingly, toner T does not adhere to pressing roller 120 after the outlet of fixing nip part N due to the elasticity, as a result, the winding of paper P round pressing roller 120 can be prevented.

In addition, the winding of paper P round pressing roller 120 can be prevented, so that it is not necessary to forcibly peel paper P from pressing roller 120. Accordingly, when paper P peels off pressing roller 120 after the outlet of fixing nip part N, hot offset by the reluctance of separation of toner T' can also be prevented.

Contrary to this, when initial relaxation modulus  $G(t=0.01)$  [Pa] of toner T at 120°C is smaller than  $1.0 \times 10^5$  [Pa], the elasticity of the toner (hardness) is insufficient, the melted toner adheres to the surface of pressing roller 120, and the toner does not sufficiently

peel off the surface of pressing roller 120, as a result the winding of paper P round pressing roller 120 is brought about. And when paper P is forcedly peeled off by means of releasing pawl, there is the possibility that hot offset occurs due to the reluctance of separation of the toner for lack of elasticity.

On the other hand, in the heat-fixing unit in which the toner of the first invention is used, heating fixation is performed from the backside of the fixing surface of the toner via a recording medium, so that the toner cannot be heated directly. However, the ratio of the initial relaxation modulus  $G(t=0.01)$  (Pa) to the relaxation modulus  $G(t=0.1)$  (Pa) in relaxation time of 0.1 sec at 180°C of the toner of the first invention,  $[G(t=0.01)/G(t=0.1)]$ , is set at 20 or more. Accordingly, the toner melts almost completely in fixing nip. Therefore, good fixing property that does not bring about hot offset can be secured.

Thus according to the toner of the first invention, good fixing characteristics can be secured even with an oil-less fixing unit, and the winding of paper P round pressing roller 120 in backside heating fixation can also be prevented by organically combining the fixing nip configuration protruding toward the side of main heating member, performing heating fixation from the backside of

the fixing surface of the toner, setting initial relaxation modulus of the toner at 120°C,  $G(t=0.01)$  [Pa], at  $1.0 \times 10^5$  [Pa] or higher, and setting the ratio of the initial relaxation modulus  $G(t=0.01)$  (Pa) to the relaxation modulus  $G(t=0.1)$  (Pa) in relaxation time of 0.1 sec at 180°C of the toner,  $[G(t=0.01)/G(t=0.1)]$ , at 20 or more.

Although toner T of the first invention is in contact with pressing roller 120, toner T is fixed on paper P without adhering to pressing roller 120 (without causing offset) by the increase of elasticity and viscosity. Since toner T of the first invention is excellent in offset resistance at high temperature, it is not necessary to coat a release agent, e.g., silicone oil, on the surface of pressing roller 120.

In the toner of the second invention constituted as above, when a toner image by this toner is fixed by backside heating with, e.g., a fixing unit as shown in Fig. 2 (a) and (b), unfixed toner T of the toner image on paper P is fixed by heating from the backside with a main heating member heating roller 210. Since fixing nip part N takes the configuration protruding toward the side of pressing roller 220, paper P is discharged from the outlet of fixing nip part N along by the line of the protruding configuration of nip part N. Therefore, fixed toner T' on the recording medium tries to move along by heating roller

210. And the temperature of heating-fixed toner T' on paper P discharged from the fixing nip outlet lowers.

In stress relaxation measurement, initial relaxation modulus  $G(t=0.01)$  (Pa) in relaxation time of 0.01 (sec) of the starting time of measuring stress relaxation at 120°C, the temperature lowered after being discharged from the outlet of fixing nip part N, of the toner of the second invention is: initial relaxation modulus  $G(t=0.01)$  [Pa]  $\geq 1.0 \times 10^5$  [Pa], thus, toner T melted in fixing nip part N is brought to have relatively sufficient elasticity after being discharged from the outlet of fixing nip part N. Accordingly, toner T does not adhere to pressing roller 220 after the outlet of fixing nip part N due to the elasticity, as a result, the winding of paper P round pressing roller 220 can be prevented.

In addition, the winding of paper P round pressing roller 220 can be prevented, so that it is not necessary to forcibly peel paper P from pressing roller 220. Accordingly, when paper P peels off pressing roller 220 after the outlet of fixing nip part N, hot offset by the reluctance of separation of toner T' can also be prevented.

Contrary to this, when initial relaxation modulus  $G(t=0.01)$  [Pa] of toner T at 120°C is smaller than  $1.0 \times 10^5$  [Pa], the elasticity of the toner (hardness) is insufficient, the melted toner adheres to the surface of

pressing roller 220, and the toner does not sufficiently peel off the surface of pressing roller 220, as a result the winding of paper P round pressing roller 220 is brought about. And when paper P is forcedly peeled off by means of  
5 releasing pawl, there is the possibility that hot offset occurs due to the reluctance of separation of the toner for lack of elasticity.

On the other hand, if the elasticity of the toner is too small when the toner is heated before the outlet of  
10 fixing nip, the toner hardens with difficulty even if cooled after the nip outlet. Accordingly, there is the possibility that hot offset due to the reluctance of separation of the toner occurs. By setting initial relaxation modulus  $G(t=0.01)$  [Pa] at  $180^{\circ}\text{C}$  at  $1.0 \times 10^4$  [Pa]  
15 or higher, the elasticity of the toner before fixing nip outlet is restricted so as not to lower than a certain degree. By this contrivance, the toner appropriately hardens and hot offset due to the reluctance of separation of the toner does not occur when cooled after the nip  
20 outlet.

Thus according to the toner of the second invention, good fixing characteristics can be secured even with an oil-less fixing unit, and the winding of the recording medium round the pressing member in backside heating  
25 fixation can also be prevented by organically combining the

fixing nip configuration protruding toward the side of pressing roller 20, performing heating fixation from the backside of the fixing surface of the toner, setting initial relaxation modulus of the toner at 120°C, G  
5 (t=0.01) [Pa], at  $1.0 \times 10^5$  [Pa] or higher, and setting initial relaxation modulus of the toner at 180°C, G (t=0.01) [Pa], at  $1.0 \times 10^4$  [Pa] or higher.

Although toner T of the second invention is in contact with pressing roller 220, toner T is fixed on paper  
10 P without adhering to pressing roller 220 (without causing offset) by the increase of elasticity and viscosity. Since toner T of the second invention is excellent in offset resistance at high temperature, it is not necessary to coat a release agent, e.g., silicone oil, on the surface of  
15 pressing roller 220.

Further, The toner of the present invention may contain a charge controlling agent (CCA), and if necessary, a release agent, a dispersant, and magnetic particles. These compounds may be arbitrarily blended by kneading  
20 after forming the resin.

Charge controlling agents (CCA) are not particularly restricted, and various kinds of organic and inorganic compounds can be used so long as they can give positive or negative charge by frictional electrification.

25 As the examples of positive charge controlling agents,



e.g., ~~Nigrosine-Base~~NIGROSINE BASE EX (manufactured by Orient Chemical Industry Co., Ltd.), quaternary ammonium salt P-51 (manufactured by Orient Chemical Industry Co., Ltd.), ~~Nigrosine-Bontron~~NIGROSINE BONTRON N-01 (manufactured by Orient Chemical Industry Co., Ltd.), ~~Sudan Chief-Schwartz~~SUDAN CHIEF SCHWARTZ BB (Solvent Black 3: Color Index 26150), ~~Fetschwartz~~FETSCHWARTZ HBN (C.I. No. 26150), ~~Brilliant-Spirits-Schwartz~~BRILLIANT SPIRITS SCHWARTZ TN (manufactured by Farben Fabriken Bayer A.G.), and ~~Zapon-Schwartz~~ZAPON SCHWARTZ X (manufactured by Farberke Hoechst A.G.), in addition, alkoxylated amine, alkylamide, and molybdic acid chelate pigments are exemplified. Of these compounds, quaternary ammonium salt P-51 is preferably used.

As the examples of negative charge controlling agents, e.g., ~~Oil-Black~~OIL BLACK (Color Index 26150), ~~Oil-Black~~OIL BLACK BY (manufactured by Orient Chemical Industry Co., Ltd.), ~~Bontron~~BONTRON S-22 (manufactured by Orient Chemical Industry Co., Ltd.), salicylic acid metal complex E-81 (manufactured by Orient Chemical Industry Co., Ltd.), thioindigo series pigments, sulfonamide derivatives of copper phthalocyanine, ~~Spiron-Black~~SPIRON BLACK TRH (manufactured by HODOGAYA CHEMICAL Co., Ltd.), ~~Bontron~~BONTRON S-34 (manufactured by Orient Chemical Industry Co., Ltd.), , ~~Nigrosine~~NIGROSINE SO (manufactured by Orient

Chemical Industry Co., Ltd.), ~~Celessechwartz~~-CELESSCHWARTZ  
(R) G (manufactured by Farben Fabriken Bayer A.G.),  
~~Chromogenschwartz~~-CHROMOGENSCHWARTZ ETOO (C.I. No. 14645),  
and ~~Azo Oil Black~~AZO OIL BLACK (R) (manufactured by

5 National Aniline Co.) are exemplified. Of these compounds,  
salicylic acid metal complex E-81 is preferably used.

These charge controlling agents can be used either  
individually or as a combination of two or more thereof,  
and the addition amount of charge controlling agents added  
10 to a binder resin is from 0.001 to 5 parts by weight per  
100 parts by weight of the binder resin, preferably 0.001  
to 3 parts by weight.

The resins having a urethane and a urea bond and  
polyester resins which are used in the toner of the  
15 invention are excellent in heat melt characteristics  
according to the molecular weight range, and a release  
agent is not necessary by the viscoelastic characteristics  
in the fixing temperature range, but when a release agent  
is used, the amount is 3 parts by weight (3 wt.%) or less  
20 per 100 parts by weight of the binder resin, and preferably  
from 0 to 2 parts by weight.

Thus not only hot offset of the toner and winding of  
a recording medium can be effectively prevented, but also a  
good transparent image can be obtained by setting the  
25 content of a release agent at 3% or less to thereby reduce

the content, or even when a release agent is not used.

The specific examples of release agents include paraffin waxes, polyolefin waxes, modified waxes having an aromatic group, hydrocarbon compounds having an alicyclic group, natural waxes, long chain carboxylic acids having a long chain hydrocarbon chain having 12 or more carbon atoms [ $\text{CH}_3(\text{CH}_2)_{11}$  or  $\text{CH}_3(\text{CH}_2)_{12}$  or higher aliphatic carbon chain], the esters thereof, metal salts of fatty acid, fatty acid amide and fatty acid bisamide. Compounds having different softening temperatures may be used as mixture. The specific examples of paraffin waxes include paraffin waxes (manufactured by NIPPON OIL COMPANY LIMITED), paraffin waxes (manufactured by Nippon Seiro Co., Ltd.), micro-wax waxes (manufactured by NIPPON OIL COMPANY LIMITED), micro-crystalline waxes (manufactured by Nippon Seiro Co., Ltd.), hard paraffin waxes (manufactured by Nippon Seiro Co., Ltd.), PE-130 (manufactured by Hoechst A.G.), ~~Mitsui Hi-Wax~~ MITSUI HI-WAX 110P (manufactured by Mitsui Petrochemical Industries, Ltd.), ~~Mitsui Hi-Wax~~ MITSUI HI-WAX 220P (manufactured by Mitsui Petro-chemical Industries, Ltd.), ~~Mitsui Hi-Wax~~ MITSUI HI-WAX 660P (manufactured by Mitsui Petrochemical Industries, Ltd.), ~~Mitsui Hi-Wax~~ MITSUI HI-WAX 210P (manufactured by Mitsui Petrochemical Industries, Ltd.), ~~Mitsui Hi-Wax~~ ~~320P~~ ~~Mitsui Hi-Wax~~ MITSUI HI-WAX 320P MITSUI HI-WAX 410P (manufactured by

Mitsui Petrochemical Industries, Ltd.), ~~Mitsui Hi-Wax~~MITSUI  
HI-WAX 420P (manufactured by Mitsui Petrochemical  
Industries, Ltd.), ~~modified wax~~MODIFIED WAX JC-1141  
(manufactured by Mitsui Petrochemical Industries, Ltd.),  
5 ~~modified wax~~MODIFIED WAX JC-2130 (manufactured by Mitsui  
Petrochemical Industries, Ltd.), ~~modified wax~~MODIFIED WAX  
JC-4020 (manufactured by Mitsui Petrochemical Industries,  
Ltd.), ~~modified wax~~MODIFIED WAX JC-1142 (manufactured by  
Mitsui Petrochemical Industries, Ltd.), ~~modified~~  
10 ~~wax~~MODIFIED WAX JC-5020 (manufactured by Mitsui  
Petrochemical Industries, Ltd.), beeswax, ~~earnauba-~~  
~~wax~~CARNAUBA WAX and ~~montan wax~~MONTAN WAX. As fatty acid  
metal salts, zinc stearate, calcium stearate, magnesium  
stearate, zinc oleate, zinc palmitate, and magnesium  
15 palmitate are exemplified.

As polyolefin waxes, e.g., low molecular weight  
polypropylene, low molecular weight polyethylene, oxidation  
type polypropylene and oxidation type polyethylene are  
exemplified. The specific examples of polyolefin-based  
20 waxes include non-oxidation type polyethylene waxes, e.g.,  
~~Hoechst Wax~~HOECHST WAX PE520, ~~Hoechst Wax~~HOECHST WAX PE130,  
~~Hoechst Wax~~HOECHST WAX PE190 (manufactured by Hoechst A.G.),  
~~Mitsui Hi-Wax~~MITSUI HI-WAX 200, ~~Mitsui Hi-Wax~~MITSUI HI-WAX  
210, ~~Mitsui Hi-Wax~~MITSUI HI-WAX 210M, ~~Mitsui Hi-Wax~~MITSUI  
25 HI-WAX 220, ~~Mitsui Hi-Wax~~MITSUI HI-WAX 220M (manufactured

by Mitsui Petrochemical Industries, Ltd.), and SANWAX 131-P, SANWAX 151-P, SANWAX 161-P (manufactured by Sanyo Chemical Industries Co., Ltd.), oxidation type polyethylene waxes, e.g. ~~Hoechst-Wax~~HOECHST WAX PED121, ~~Hoechst-Wax~~HOECHST WAX PED153, ~~Hoechst-Wax~~HOECHST WAX PED521, ~~Hoechst-Wax~~HOECHST WAX PED522, ~~Hoechst-Wax-Ceridust~~HOECHST WAX CERIDUST 3620, ~~Hoechst-Wax-Ceridust~~HOECHST WAX CERIDUST VP130, ~~Hoechst-Wax-Ceridust~~HOECHST WAX CERIDUST VP5905, ~~Hoechst-Wax-Ceridust~~HOECHST WAX CERIDUST VP9615A, ~~Hoechst-Wax-Ceridust~~HOECHST WAX CERIDUST TM9610F, ~~Hoechst-Wax-Ceridust~~HOECHST WAX CERIDUST 3715 (manufactured by Hoechst A.G.), ~~Mitsui-Hi-Wax~~MITSUI HI-WAX 420M (manufactured by Mitsui Petrochemical Industries, Ltd.), and SANWAX E-300, SANWAX E-250P (manufactured by Sanyo Chemical Industries Co., Ltd.), non-oxidation type polypropylene waxes, e.g., ~~Hoechst-Wachs~~HOECHST WACHS PP230 (manufactured by Hoechst A.G.), VISCOL 330-P, VISCOL 550-P, VISCOL 660-P, (manufactured by Sanyo Chemical Industries Co., Ltd.), and oxidation type polypropylene waxes, e.g., VISCOL TS-200 (manufactured by Sanyo Chemical Industries Co., Ltd.).

These release agents can be used alone or in combination of two or more. As the release agent added according to necessity, it is preferred to use a compound having a softening temperature (a melting temperature) of from 40 to 130°C, preferably from 50 to 120°C. A softening temperature


is an endothermic main peak value on the DSC endothermic curve measured with "DSC120" (a product of Seiko Instruments Inc.).

The mother particles of the toner of the present invention can be obtained by kneading the above compositions, melting, then pulverizing the obtained product by finely grinding member and classifying. A flowability improver may be externally added to the compositions for improving the flowability.

Organic and inorganic fine particles can be used as the flowability improver. For instance, fluorine resin powders, e.g., vinylidene fluoride fine powders, polytetrafluoroethylene fine powders, acrylate resin fine powders; fatty acid metal salts, e.g., zinc stearate, calcium stearate, lead stearate; metal oxides, e.g., iron oxide, aluminum oxide, titanium oxide, zinc oxide; and surface-treated silica obtained by treating silica fine powders manufactured by a wet or dry manufacturing process with a silane coupling agent, a titanium coupling agent or a silicone oil, are exemplified as flowability improvers. These compounds are used either individually or as a combination of two or more thereof.

Preferred flowability improvers are fine powders manufactured by a vapor phase oxidation method of a silicon halogen compound, i.e., so-called dry process silica or

fumed silica, which can be manufactured by well-known methods, for example, a method which utilizes heat decomposition oxidation reaction in oxyhydrogen flame of silicon tetrachloride gas, and fundamental reaction formula  
5 is as follows.



Further, in this manufacturing process, it is also possible to obtain complex fine powders of silica with other metal oxides by using other metal halogen compounds,  
10 e.g., aluminum chloride or titanium chloride, together with a silicon halogen compound, and these complex fine powders are also included in the scope of the invention. It is preferred for these silica fine powders to have an average primary particle size of from 0.001 to 2  $\mu\text{m}$ , particularly  
15 preferably from 0.002 to 0.2  $\mu\text{m}$ . As commercially available silica fine powders manufactured by a vapor phase oxidation method of a silicon halogen compound that are used in the present invention, the following commercial products are exemplified. For instance, AEROSIL 130, AEROSIL 200,  
20 AEROSIL 300, AEROSIL 380, TT600, MOX170, MOX80, and COK84 (manufactured by Nippon Aerosil Co., Ltd.), ~~Ca-O-Si-L-M-5CA-~~  
O-SIL M-5, MS-7, MS-75, HS-5 and EH-5 (manufactured by CABOT Co.), ~~Wacker~~ WACKER HDK N20 V15, N20E, T30 and T40 (manufactured by WACKER-CHEMIE GMBH), ~~D-C Fine Silica~~ D-C  
25 FINE SILICA (manufactured by Dow Corning Co.), and Fransol

(manufactured by Fransil Co.) are exemplified.

It is more preferred to use the silica fine powders manufactured by a vapor phase oxidation method of a silicon halogen compound subjected to hydrophobitization treatment.

5 Of the hydrophobitization-treated silica fine powders, those treated so as to have a hydrophobitization degree measured by a methanol titration test of from 30 to 80 are particularly preferred. The hydrophobitization treatment is performed by chemically treating the silica fine powders  
10 with organic silicon compounds that react with the silica fine powders or physically adsorbed onto the silica fine powders. A preferred method is treating the silica fine powders manufactured by a vapor phase oxidation method of a silicon halogen compound with an organic silicon compound.

15 The examples of such organic silicon compounds include hexamethyldisilazane, trimethylsilane, trimethylchlorosilane, trimethylethoxysilane, dimethyldichlorosilane, methyltrichlorosilane, allyldimethylchlorosilane, allylphenyldichlorosilane,  
20 benzyldimethylchlorosilane, bromomethyldimethylchlorosilane,  $\alpha$ -chloroethyltrichlorosilane,  $\beta$ -chloroethyltrichlorosilane, chloromethyldimethylchlorosilane, triorganosilylmercaptan, trimethylsilylmercaptan, triorganosilyl acrylate, vinyl dimethylacetoxysilane, dimethylethoxysilane,  
25 dimethyldimethoxysilane, diphenyldiethoxysilane,



hexamethyldisiloxane, 1,3-divinyltetramethyldisiloxane, 1,3-diphenyldisiloxane, and dimethylpolysiloxane having from 2 to 12 siloxane units per a molecule, wherein every unit at terminal has a hydroxyl group bonded to Si.

5 These compounds are used either individually or a combination of two or more thereof.

Silica fine powders subjected to hydrophobitization treatment have a particle size of from 0.003 to 0.1  $\mu\text{m}$ , preferably from 0.005 to 0.05  $\mu\text{m}$ . As commercially  
10 available products, there are ~~Taranocks~~ TARANOCKS 500 (manufactured by Tarco Co.) and AEROSIL R-972 (manufactured by Nippon Aerosil Co., Ltd.).

The addition amount of flowability improvers is from 0.01 to 5 parts by weight per 100 parts by weight of the  
15 binder resin, preferably from 0.1 to 3 parts by weight. When the addition amount is less than 0.01 parts by weight, flowability is not improved, and when it is more than 5 parts by weight, fog or blotting occurs or the scattering of the toner in the machine is accelerated.

20

The manufacturing method of the toner in the present invention is described above with respect to the manufacture of binder polymers (binder resins), and the manufacturing process fundamentally comprises the following  
25 steps.

(1) Uniform blending of materials

Prescribed amounts of additives, e.g., a binder resin, a charge controlling agent and the like are introduced into a ~~Henschel mixer~~ HENSCHEL MIXER 20B

5 (manufactured by MITSUI MINING COMPANY, LIMITED) and blended uniformly.

(2) Dispersion and fixation of each additive in binder resin

After these materials are uniformly blended, they  
10 are melt-kneaded with a two-shaft kneading-extruder (PCM-30, manufactured by Ikegai), and each component is dispersed and fixed in the binder resin. As other melt-kneading member, continuous kneaders, such as "TEM-37 (manufactured by TOSHIBA MACHINE CO., LTD.) and "KRC Kneader"  
15 (manufactured by KURIMOTO, LTD.), and batch kneaders, such as heating and pressing kneaders are exemplified.

(3) Pulverization

After the kneaded product is coarsely pulverized and particle sizes are adjusted, the product is finely  
20 pulverized by impinging by jet air with a jet pulverizer "200AFG" (manufactured by HOSOKAWA MICRON CORPORATION), or "IDS-2" (manufactured by Nippon Pneumatic Mfg. Co., Ltd.) to make average particle size from 1 to 8  $\mu$ m. As other grinding member, mechanical grinder ~~Turbo-Mill~~ TURBO MILL  
25 (manufactured by Kawasaki Heavy Industries, Ltd.) and ~~Super~~

~~Rotor~~SUPER ROTOR (manufactured by Nisshin Engineering) are exemplified.

#### (4) Classification

After removing fine powders, for the purpose of making particle size distribution narrow, the pulverized product is subjected to particle size adjustment by air classification or rotor revolution with air classifier "100 ATP (manufactured by HOSOKAWA MICRON CORPORATION), "DSX-2" (manufactured by Nippon Pneumatic Mfg. Co., Ltd.), or  
10 ~~"Elbow Jet"~~ "ELBOW JET" (manufactured by NITTETSU MINING CO., LTD.).

#### (5) Addition of external additives

The obtained colored resin particles and a fluidizing agent are introduced each in a prescribed amount into a ~~Henschel mixer~~ HENSCHEL MIXER 20B (manufactured by  
15 MITSUI MINING COMPANY, LIMITED) and uniformly blended, thereby a toner is obtained.

The thus-obtained toners have an average particle size of from 3 to 10  $\mu\text{m}$ , and preferably from 5 to 8  $\mu\text{m}$ , by which high precision can be given. The degree of  
20 circularity is from 0.93 to 0.99, and preferably from 0.94 to 0.98, by which toners have excellent flowing and cleaning properties.

Well-known methods can be applied to the measurement  
25 of the physical properties of the toner of the invention,

e.g., softening temperature ( $T_m$ ), glass transition temperature ( $T_g$ ), molecular weight, particle size, storage modulus  $G'$ , loss modulus  $G''$  and relaxation modulus  $G(t)$ , and the evaluation of good offset region of the toner at  
5 fixing time, and examples of these methods are described in Examples and Comparative Examples later.

The toners of the present invention are specifically described with reference to Examples and Comparative  
10 Examples.

In the first place, measuring methods of physical properties in Examples of the present invention and Comparative Examples, and the evaluation of good region of offset of a toner at fixing time are described.

15

(1) Measurement of softening temperature

( $T_m$ , melting temperature) ( $^{\circ}\text{C}$ )

The measurement is performed with constant load extrusion capillary rheometer, ~~Flow Tester~~FLOW TESTER CFD-  
20 500D (manufactured by Shimadzu Corporation) by the following conditions.

Preparation of a measuring sample:

As the measuring sample, about 1 g of a toner is compression-molded to make a cylindrical sample  
25 fitting in with the inside diameter of the cylinder

of ~~Flow Tester~~ FLOW TESTER.

Measuring conditions:

Load: 20 kgf, pit of the die: 1 mm,  
and length of the die: 1 mm

5 Measuring method:

A 1/2 method

Preheating time:

300 seconds

Starting temperature of measurement:

10 50°C

Velocity of temperature up:

5°C/min

T<sub>m</sub>:

The endothermic peak corresponding to crystalline  
15 melting temperature (softening temperature) is taken  
as T<sub>m</sub>.

(2) Measurement of glass transition temperature (T<sub>g</sub>) (°C)

Ten (10) mg of a toner is packed in an aluminum cell,  
20 and the glass transition temperature is measured with  
"DSC120" (manufactured by Seiko Instruments Inc.) by the  
following conditions.

Measuring temperature:

From 20°C (starting temperature of measurement) to  
25 200°C (termination temperature of measurement)

Velocity of temperature up:

10°C/min

Tg:

From DSC curve that once temperature was raised and  
5 the previous hysteresis was erased, the temperature  
of the shoulder of the endothermic curve where heat  
absorption corresponding to glass transition  
temperature occurs is taken as Tg.

10 (3) Measurement of molecular weight and molecular weight  
distribution:

Preparation of sample:

About 10 mg of a toner is dissolved in about 10 ml  
of THF. The insoluble contents in THF were removed  
15 through a membrane filter having a pore size of 0.2  
µm, to thereby obtain a sample for GPC.

Measuring instrument:

HLC-8220GPC (manufactured by TOSO CORPORATION)

Column:

20 TSK ~~Gel-Super~~GEL SUPER HZM-M (manufactured by TOSO  
CORPORATION)

Temperature:

40°C

Eluate:

25 Tetrahydrofuran (THF, manufactured by KANTO KAGAKU)

Flow velocity:

0.35 ml/min

Detector:

UV detector (wavelength of detection: 254 nm)

5 Standard sample:

Standard polystyrene (manufactured by TOSO  
CORPORATION)

(4) Measurement of particle size (D50):

10 In the specification of the present invention,  
particle size member "average particle size D50".

Particle size is obtained by measuring relative  
weight distribution by particle size with Coulter-  
~~Multisizer model~~ COULTER MULTISIZER MODEL III (manufactured  
15 by Beckman Coulter, Inc.) and 100  $\mu$ m aperture tube.  
Further, the particle sizes of external additives, e.g.,  
silica particles, are measured with an electron microscope.

(5) Measurement of relaxation modulus (t) [Pa]

20 The relaxation modulus G (t) Pa of the toner of the  
invention is obtained by the measurement of viscoelasticity  
with a viscoelasticity measuring instrument shown in Fig. 1  
(a) by stress relaxation measuring mode (that is, stress  
relaxation measurement) by the following conditions. Here,  
25 stress relaxation measuring mode is a method of suddenly

applying previously set quantity of strain to a measuring toner sample, and measuring the stress necessary to maintain the strain by the time elapse. Further, a value obtained by dividing the stress varying by the time elapse  
5 by certain strain is the storage modulus  $G(t)$  [Pa].

In the present invention, initial relaxation modulus  $G(t=0.01)$  Pa in relaxation time of 0.01 (sec), which is the starting time of measuring stress relaxation, at 120°C and 180°C considering the reduction of the temperature of  
10 the toner after paper discharge from the fixing nip part are found.

Viscoelasticity measuring instrument:

Viscoelasticity measuring instrument is ARES viscoelasticity measuring system (ARES  
15 viscoelasticity measuring instrument, manufactured by Rheometric Scientific F.E. Company).

Measuring temperature:

Measuring temperature is set at 120°C and 180°C.

Geometry:

20 Two parallel plates of top and bottom ( $\phi 25$  mm)

Preparation of measuring sample:

About 1 g of a compaction molded toner is put on the bottom plate of the parallel plates, the toner is heated with a heater to the measuring temperature,  
25 and the top plate of the parallel plates is put on



the toner to press the toner when the toner becomes a little soft. As is shown in Fig. 4 (b), the toner protruding from the parallel plates is removed by trimming, the toner is fitted in with the peripheral shape of the parallel plates (i.e., the diameter of the parallel plates), and the height of the sample is adjusted to 1.0 to 2.0 mm (the gap between the top and bottom plates) as shown in Fig. 4 (a), to thereby prepare a cylindrical sample. As is shown in Fig. 4 (c), when the toner is not adhered on the entire surface of the top and bottom plates, the toner is not used as a measuring sample, as not good (NG).

#### Quantity of applied strain:

Strain is given to the toner by revolving the bottom plate of the parallel plates. At this time the measuring temperature is maintained constant, and gradually greater strain (frequency: 1 (rad/sec) (1 rad/sec =  $(1/6.28)$  Hz, strain: from 0.1 to 200%) is given to the measuring sample by strain sweep mode. The maximum strain in the linear region of storage modulus  $G'$  and loss modulus  $G''$  of dynamic viscoelasticity to the given strain is taken as measuring strain at relaxation modulus measuring time.

Measuring mode:

Viscoelasticity measurement is performed by stress relaxation measuring mode.

- 5 (6) Measurement of diameters of heating roller and pressing roller

Diameters of heating roller and pressing roller were measured with calipers.

- 10 (7) Measurement of nip breadth

The temperature of the fixing unit is set at 140°C, the fixing unit is stopped in the middle of the transition of OHP sheet across the fixing unit, and OHP sheet is held in the nip, after allowing to stand for 3 minutes, OHP  
15 sheet is taken out. The trace of nip breadth left on OHP sheet is measured with calipers accurately and the trace is taken as the nip breadth of the fixing unit.

- (8) Evaluating method of winding

20 A solid image (adhered amount of the toner: 0.4 mg/cm<sup>2</sup>) is formed on common paper S for PPC (manufactured by FUJI XEROX OFFICE SUPPLY) with LP-3000C (manufactured by Seiko Epson Corporation) from which a fixing part is detached. The solid image is passed through the fixing  
25 unit having the rollers of diameters as shown at prescribed

temperature (180°C) and prescribed fixing nip-transiting time (40 msec). Winding of the paper around the roller is evaluated by visually observing whether the paper winds around the roller of the fixing unit or not. The fixing unit each shown in Fig. 1 and Fig. 2 are used in the first invention and the second invention, respectively.

(9) Evaluation of good region of offset at fixing time

An unfixed patch of a square region of 2 cm x 2 cm is formed at 10 mm from the end of common paper S for PPC (manufactured by FUJI XEROX OFFICE SUPPLY) by uniformly adhering a toner (adhered amount of the toner: 0.4 mg/cm<sup>2</sup>) with LP-3000C (manufactured by Seiko Epson Corporation) from which a fixing part is detached. The unfixed patch is passed through the fixing unit described in Fig. 1 having the rollers of diameters as shown at prescribed fixing nip-transiting time (40 msec).

Paper S is passed with varying the temperature from 120 to 200°C. The temperature range which does not leave low temperature or hot offset trace on the paper of the part lower by the circumference of the fixing roller from the position of the fixed patch is taken as a good region of offset by visual judgment.

(10) Measuring method of transparency (HAZE value)

An unfixed patch of 2 cm x 2 cm is formed on OHP sheet (Xerox Film, A4 size with no frame) (adhered amount of the toner: 0.4 mg/cm<sup>2</sup>) with LP-3000C (manufactured by Seiko Epson Corporation) from which a fixing part is  
5 detached. The unfixed patch is passed through the fixing unit described in Fig. 1 having the rollers of diameters as shown at prescribed temperature (180°C) and prescribed fixing nip-transiting time (40 msec). The fixed patch is measured with a turbidimeter (Model 1001DP, manufactured by  
10 Nippon Denshoku Industries Co., Ltd.). The smaller the HAZE value, the more transparent is the patch.

## EXAMPLES

15

### First invention

Examples and Comparative Examples of the toners of the first invention are described below. The fixing unit described in Fig. 1 was used in the fixation by the toners  
20 in Examples and Comparative Examples.

The manufacture of the resins for the toners of the first invention used in Examples and Comparative Examples is described below.

### Resin 1A

A mixture comprising 30 molar parts of neopentyl alcohol, 30 molar parts of ethylene glycol, 30 molar parts of 1,4-cyclohexanediol, 85 molar parts of dimethyl terephthalate, and 15 molar parts of phthalic anhydride was prepared.

A two-liter four-necked flask was equipped with a reflux condenser, a distillation column, a water separator, a nitrogen gas introducing pipe, a thermometer and a stirrer according to an ordinary method, charged with 1,000 g of the above mixture and 1 g of an esterification condensation catalyst, and esterification reaction was carried out with bleeding water and methanol generated at 180°C from the distillation column. At the point when water and methanol stopped bleeding from the distillation column, the distillation column was detached from the two-liter four-necked flask and a vacuum pump was connected to the four-necked flask. The pressure in the system was lowered to 5 mmHg or less and the reaction system was stirred at a rotary speed of 150 rpm at 200°C. Free diol generated by the condensation reaction was discharged from the system, and the thus-obtained reaction product was taken as resin 1A. Resin 1A had a softening temperature ( $T_m$ ) of 113°C, a glass transition temperature ( $T_g$ ) of 62°C, and a weight average molecular weight ( $M_w$ ) of 10,000.

## Resin 2A

A mixture comprising 80 molar parts of resin 1A, 10 molar parts of 1,4-butanediol, and 10 molar parts of dimethyl terephthalate was prepared.

A two-liter four-necked flask was equipped with a reflux condenser, a distillation column, a water separator, a nitrogen gas introducing pipe, a thermometer and a stirrer according to an ordinary method, charged with 1,000 g of the above mixture and 1 g of an esterification condensation catalyst, and esterification reaction was carried out with bleeding water and methanol generated at 200°C from the distillation column. At the point when water and methanol stopped bleeding from the distillation column, the distillation column was detached from the two-liter four-necked flask and a vacuum pump was connected to the four-necked flask. The pressure in the system was lowered to 5 mmHg or less and the reaction system was stirred at a rotary speed of 150 rpm at 220°C. Free diol generated by the condensation reaction was discharged from the system, and the thus-obtained reaction product was taken as resin 2A. Resin 2A had a softening temperature ( $T_m$ ) of 167°C, a glass transition temperature ( $T_g$ ) of 66°C, and a weight average molecular weight ( $M_w$ ) of 29,000.

### Example 1A

To 100 parts by weight of resin 2A was added 20 parts by weight of pigment ~~Toner-Magenta~~TONER MAGENTA E02 (manufactured by Clariant Japan K.K.) as the colorant. The  
5 mixture was thoroughly blended by a ~~Henschel-mixer~~HENSCHEL MIXER and kneaded with a continuous system twin roll kneader (manufactured by MITSUI MINING COMPANY, LIMITED). The kneaded product was coarsely pulverized to a particle size of about 2 mm with a pulverizer (manufactured by  
10 HOSOKAWA MICRON CORPORATION), thereby a master batch was obtained.

To 30 parts by weight of the above-obtained master batch, 76 parts by weight of resin 1A, and 1 part by weight of ~~Bontren~~BONTRON E-84 (manufactured by Orient Chemical  
15 Industry Co., Ltd.) as CCA were added and thoroughly blended with a HENSCHEL MIXER~~Henschel-mixer~~, and melt-kneaded with a two-shaft extruder (manufactured by TOSHIBA MACHINE CO., LTD.), cooled to normal temperature (25°C), pulverized and classified with the above pulverizer and  
20 classifier (manufactured by HOSOKAWA MICRON CORPORATION), thereby mother particles having weight D50 of 8 µm were obtained. To 100 parts by weight of the mother particles, 1.0 part by weight of silica RX200 (manufactured by Nippon Aerosil Co., Ltd.) was added and blended with a ~~Henschel-~~  
25 ~~mixer~~HENSCHEL MIXER, thereby a toner in Example 1A was

obtained.

The diameter of the heating roller (HR) of the fixing unit used in the fixation by the toner in Example 1A is 30 mm, and the diameter of the pressing roller (PR) is 35 mm, and the fixing nip breadth at this time is 8.4 mm.

#### Example 2A

To 100 parts by weight of resin 2A was added 20 parts by weight of pigment ~~Toner-Magenta~~TONER MAGENTA E02 (manufactured by Clariant Japan K.K.) as the colorant. The mixture was thoroughly blended by a ~~Henschel-mixer~~HENSCHEL MIXER and kneaded with the above continuous system twin roll kneader. The kneaded product was coarsely pulverized to a particle size of about 2 mm with the above pulverizer, to thereby obtain a master batch.

To 30 parts by weight of the above-obtained master batch, 76 parts by weight of resin 1A, 1 part by weight of ~~Bontren~~BONTRON E-84 (manufactured by Orient Chemical Industry Co., Ltd.) as CCA, and 1 part by weight of ~~earnauba-wax~~CARNAUBA WAX (manufactured by NIPPON WAX CORPORATION) as the release agent were added and thoroughly blended with a ~~Henschel-mixer~~HENSCHEL MIXER, and melt-kneaded with the above two-shaft extruder, cooled to normal temperature (25°C), pulverized and classified with the above pulverizer and classifier, thereby mother particles



having weight D50 of 8  $\mu$ m were obtained. To 100 parts by weight of the mother particles, 1.0 part by weight of silica RX200 (manufactured by Nippon Aerosil Co., Ltd.) was added and blended with a HENSCHEL MIXER~~Henschel mixer~~,  
5 thereby a toner in Example 2A was obtained.

The diameter of the heating roller (HR) of the fixing unit used in the fixation by the toner in Example 2A is 20 mm, and the diameter of the pressing roller (PR) is 25 mm, and the fixing nip breadth at this time is 7.0 mm.  
10

#### Example 3A

To 100 parts by weight of resin 2A was added 20 parts by weight of pigment ~~Toner-Magenta~~TONER MAGENTA E02 (manufactured by Clariant Japan K.K.) as the colorant. The  
15 mixture was thoroughly blended by a HENSCHEL MIXER~~Henschel mixer~~ and kneaded with the above continuous system twin roll kneader. The kneaded product was coarsely pulverized to a particle size of about 2 mm with the above pulverizer, to thereby obtain a master batch.

20 To 30 parts by weight of the above-obtained master batch, 76 parts by weight of resin 1A, 1 part by weight of ~~Bontren~~BONTRON E-84 (manufactured by Orient Chemical Industry Co., Ltd.) as CCA, and 3 parts by weight of ~~earnauba wax~~CARNAUBA WAX (manufactured by NIPPON WAX  
25 CORPORATION) as the release agent were added and thoroughly



~~Bontren~~ BONTRON E-84 (manufactured by Orient Chemical Industry Co., Ltd.) as CCA, and 1 part by weight of ~~earnauba wax~~ CARNAUBA WAX (manufactured by NIPPON WAX CORPORATION) as the release agent were added and thoroughly  
5 blended with a ~~Henschel mixer~~ HENSCHEL MIXER, and melt-kneaded with the above two-shaft extruder, cooled to normal temperature (25°C), pulverized and classified with the above pulverizer and classifier, thereby mother particles having weight D50 of 8 µm were obtained. To 100 parts by  
10 weight of the mother particles, 1.0 part by weight of silica RX200 (manufactured by Nippon Aerosil Co., Ltd.) was added and blended with a ~~Henschel mixer~~ HENSCHEL MIXER, thereby a toner in Example 4A was obtained.

The diameter of the heating roller (HR) of the  
15 fixing unit used in the fixation by the toner in Example 4A is 30 mm, and the diameter of the pressing roller (PR) is 35 mm, and the fixing nip breadth at this time is 6.4 mm.

#### Example 5A

20 To 100 parts by weight of resin 2A was added 10 parts by weight of pigment ~~Toner Magenta~~ TONER MAGENTA E02 (manufactured by Clariant Japan K.K.) as the colorant. The mixture was thoroughly blended by a ~~Henschel mixer~~ HENSCHEL MIXER and kneaded with the above continuous system twin  
25 roll kneader. The kneaded product was coarsely pulverized

to a particle size of about 2 mm with the above pulverizer,  
to thereby obtain a master batch.

To 60 parts by weight of the above-obtained master  
batch, 46 parts by weight of resin 1A, 1 part by weight of  
5 ~~Bontren~~ BONTRON E-84 (manufactured by Orient Chemical  
Industry Co., Ltd.) as CCA, and 2 parts by weight of  
~~earnauba-wax~~ CARNAUBA WAX (manufactured by NIPPON WAX  
CORPORATION) as the release agent were added and thoroughly  
blended with a HENSCHEL MIXER ~~Henschel mixer~~, and melt-  
10 kneaded with the above two-shaft extruder, cooled to normal  
temperature (25°C), pulverized and classified with the  
above pulverizer and classifier, thereby mother particles  
having weight D50 of 8  $\mu$ m were obtained. To 100 parts by  
weight of the mother particles, 1.0 part by weight of  
15 silica RX200 (manufactured by Nippon Aerosil Co., Ltd.) was  
added and blended with a ~~Henschel mixer~~ HENSCHEL MIXER,  
thereby a toner in Example 5A was obtained.

The diameter of the heating roller (HR) of the  
fixing unit used in the fixation by the toner in Example 5A  
20 is 40 mm, and the diameter of the pressing roller (PR) is  
45 mm, and the fixing nip breadth at this time is 10.8 mm.

#### Comparative Example 1A

To 100 parts by weight of a crosslinked polyester  
25 resin (manufactured by Sanyo Chemical Industries Co., Ltd.;

softening temperature (Tm): 144°C, glass transition  
temperature (Tg): 60°C, weight average molecular weight  
(Mw): 29,000) was added 20 parts by weight of pigment Toner  
~~Magenta~~MAGENTA E02 (manufactured by Clariant Japan K.K.)  
5 as the colorant. The mixture was thoroughly blended by a  
~~HENSCHEL MIXER~~Henschel mixer and kneaded with the above  
continuous system twin roll kneader. The kneaded product  
was coarsely pulverized to a particle size of about 2 mm  
with the above pulverizer, to thereby obtain a master batch.  
10 To 30 parts by weight of the above-obtained master  
batch, 76 parts by weight of a linear polyester resin  
(manufactured by Sanyo Chemical Industries Co., Ltd.;  
softening temperature (Tm): 105°C, glass transition  
temperature (Tg): 68°C, weight average molecular weight  
15 (Mw): 11,500), 1 part by weight of BONTRON~~Bontren~~ E-84  
(manufactured by Orient Chemical Industry Co., Ltd.) as CCA,  
and 1 part by weight of ~~carnauba wax~~CARNAUBA WAX  
(manufactured by NIPPON WAX CORPORATION) as the release  
agent were added and thoroughly blended with a ~~Henschel~~  
20 ~~mixer~~HENSCHEL MIXER, and melt-kneaded with the above two-  
shaft extruder, cooled to normal temperature (25°C),  
pulverized and classified with the above pulverizer and  
classifier, thereby mother particles having weight D50 of 8  
µm were obtained. To 100 parts by weight of the mother  
25 particles, 2.0 parts by weight of silica RX200

(manufactured by Nippon Aerosil Co., Ltd.) was added and blended with a ~~Henschel-mixer~~HENSCHEL MIXER, thereby a toner in Comparative Example 1A was obtained.

The diameter of the heating roller (HR) of the  
5 fixing unit used in the fixation by the toner in Comparative Example 1A is 30 mm, and the diameter of the pressing roller (PR) is 35 mm, and the fixing nip breadth at this time is 8.4 mm.

#### 10 Comparative Example 2A

To 100 parts by weight of a crosslinked polyester resin (manufactured by Sanyo Chemical Industries Co., Ltd.; softening temperature (Tm): 144°C, glass transition temperature (Tg): 60°C, weight average molecular weight  
15 (Mw): 29,000) was added 20 parts by weight of pigment ~~Toner~~ MagentaTONER MAGENTA E02 (manufactured by Clariant Japan K.K.) as the colorant. The mixture was thoroughly blended by a ~~Henschel-mixer~~HENSCHEL MIXER and kneaded with the above continuous system twin roll kneader. The kneaded  
20 product was coarsely pulverized to a particle size of about 2 mm with the above pulverizer, to thereby obtain a master batch.

To 30 parts by weight of the above-obtained master batch, 76 parts by weight of a linear polyester resin  
25 (manufactured by Sanyo Chemical Industries Co., Ltd.;

softening temperature (Tm): 105°C, glass transition  
temperature (Tg): 68°C, weight average molecular weight  
(Mw): 11,500), 1 part by weight of BONTRON~~Bontren~~ E-84  
(manufactured by Orient Chemical Industry Co., Ltd.) as CCA,  
5 and 2 parts by weight of ~~earnauba wax~~CARNAUBA WAX  
(manufactured by NIPPON WAX CORPORATION) as the release  
agent were added and thoroughly blended with a ~~Henschel-~~  
~~mixer~~HENSCHEL MIXER, and melt-kneaded with the above two-  
shaft extruder, cooled to normal temperature (25°C),  
10 pulverized and classified with the above pulverizer and  
classifier, thereby mother particles having weight D50 of 8  
µm were obtained. To 100 parts by weight of the mother  
particles, 2.0 parts by weight of silica RX200  
(manufactured by Nippon Aerosil Co., Ltd.) was added and  
15 blended with a ~~Henschel-mixer~~HENSCHEL MIXER, thereby a  
toner in Comparative Example 2A was obtained.

The diameter of the heating roller (HR) of the  
fixing unit used in the fixation by the toner in  
Comparative Example 2A is 25 mm, and the diameter of the  
20 pressing roller (PR) is also 25 mm, and the fixing nip  
breadth at this time is 7.1 mm.

#### Comparative Example 3A

To 100 parts by weight of a crosslinked polyester  
25 resin (manufactured by Sanyo Chemical Industries Co., Ltd.;

softening temperature (Tm): 144°C, glass transition  
temperature (Tg): 60°C, weight average molecular weight  
(Mw): 29,000) was added 20 parts by weight of pigment ~~Toner~~  
~~Magenta~~TONER MAGENTA E02 (manufactured by Clariant Japan  
5 K.K.) as the colorant. The mixture was thoroughly blended  
by a ~~Henschel mixer~~HENSCHEL MIXER and kneaded with the  
above continuous system twin roll kneader. The kneaded  
product was coarsely pulverized to a particle size of about  
2 mm with the above pulverizer, to thereby obtain a master  
10 batch.

To 40 parts by weight of the above-obtained master  
batch, 68 parts by weight of a linear polyester resin  
(manufactured by Sanyo Chemical Industries Co., Ltd.;  
softening temperature (Tm): 105°C, glass transition  
15 temperature (Tg): 68°C, weight average molecular weight  
(Mw): 11,500), 1 part by weight of ~~Bontren~~BONTRON E-84  
(manufactured by Orient Chemical Industry Co., Ltd.) as CCA,  
and 3 parts by weight of ~~earnauba wax~~CARNAUBA WAX  
(manufactured by NIPPON WAX CORPORATION) as the release  
20 agent were added and thoroughly blended with a ~~Henschel~~  
~~mixer~~HENSCHEL MIXER, and melt-kneaded with the above two-  
shaft extruder, cooled to normal temperature (25°C),  
pulverized and classified with the above pulverizer and  
classifier, thereby mother particles having weight D50 of 8  
25 µm were obtained. To 100 parts by weight of the mother



particles, 2.0 parts by weight of silica RX200  
(manufactured by Nippon Aerosil Co., Ltd.) was added and  
blended with a ~~Henschel-mixer~~HENSCHEL MIXER, thereby a  
toner in Comparative Example 3A was obtained.

5           The diameter of the heating roller (HR) of the  
fixing unit used in the fixation by the toner in  
Comparative Example 3A is 40 mm, and the diameter of the  
pressing roller (PR) is 45 mm, and the fixing nip breadth  
at this time is 8.8 mm.

#### Comparative Example 4A

To 100 parts by weight of a crosslinked polyester  
resin (manufactured by Sanyo Chemical Industries Co., Ltd.;  
softening temperature (Tm): 144°C, glass transition  
15 temperature (Tg): 60°C, weight average molecular weight  
(Mw): 29,000) was added 10 parts by weight of pigment ~~Toner~~  
~~Magenta~~TONER MAGENTA E02 (manufactured by Clariant Japan  
K.K.) as the colorant. The mixture was thoroughly blended  
by a ~~Henschel-mixer~~HENSCHEL MIXER and kneaded with the  
20 above continuous system twin roll kneader. The kneaded  
product was coarsely pulverized to a particle size of about  
2 mm with the above pulverizer, to thereby obtain a master  
batch.

To 60 parts by weight of the above-obtained master  
25 batch, 46 parts by weight of a linear polyester resin

(manufactured by Sanyo Chemical Industries Co., Ltd.; softening temperature (Tm): 105°C, glass transition temperature (Tg): 68°C, weight average molecular weight (Mw): 11,500), 1 part by weight of ~~Bontren~~BONTRON E-84  
5 (manufactured by Orient Chemical Industry Co., Ltd.) as CCA, and 6 parts by weight of ~~earnauba wax~~CARNAUBA WAX (manufactured by NIPPON WAX CORPORATION) as the release agent were added and thoroughly blended with a ~~Hensehel-mixer~~HENSCHEL MIXER, and melt-kneaded with the above two-  
10 shaft extruder, cooled to normal temperature (25°C), pulverized and classified with the above pulverizer and classifier, thereby mother particles having weight D50 of 8 µm were obtained. To 100 parts by weight of the mother particles, 2.0 parts by weight of silica RX200  
15 (manufactured by Nippon Aerosil Co., Ltd.) was added and blended with a ~~Hensehel-mixer~~HENSCHEL MIXER, thereby a toner in Comparative Example 4A was obtained.

The diameter of the heating roller (HR) of the fixing unit used in the fixation by the toner in  
20 Comparative Example 4A is 30 mm, and the diameter of the pressing roller (PR) is 35 mm, and the fixing nip breadth at this time is 10.7 mm.

#### Comparative Example 5A

25 To 100 parts by weight of a crosslinked polyester

resin (manufactured by Sanyo Chemical Industries Co., Ltd.; softening temperature (Tm): 144°C, glass transition temperature (Tg): 60°C, weight average molecular weight (Mw): 29,000) was added 20 parts by weight of pigment ~~Toner~~  
5 ~~Magenta~~TONER MAGENTA E02 (manufactured by Clariant Japan K.K.) as the colorant. The mixture was thoroughly blended by a ~~Henschel-mixer~~HENSCHEL MIXER and kneaded with the above continuous system twin roll kneader. The kneaded product was coarsely pulverized to a particle size of about  
10 2 mm with the above pulverizer, to thereby obtain a master batch.

To 30 parts by weight of the above-obtained master batch, 76 parts by weight of a crosslinked polyester resin (manufactured by Sanyo Chemical Industries Co., Ltd.;  
15 softening temperature (Tm): 144°C, glass transition temperature (Tg): 60°C, weight average molecular weight (Mw): 29,000), 1 part by weight of ~~Bontren~~BONTRON E-84 (manufactured by Orient Chemical Industry Co., Ltd.) as CCA, and 5 parts by weight of ~~earnauba-wax~~CARNAUBA WAX  
20 (manufactured by NIPPON WAX CORPORATION) as the release agent were added and thoroughly blended with a ~~Henschel-mixer~~HENSCHEL MIXER, and melt-kneaded with the above two-shaft extruder, cooled to normal temperature (25°C), pulverized and classified with the above pulverizer and  
25 classifier, thereby mother particles having weight D50 of 8

um were obtained. To 100 parts by weight of the mother particles, 2.0 parts by weight of silica RX200 (manufactured by Nippon Aerosil Co., Ltd.) was added and blended with a ~~Henschel mixer~~HENSCHEL MIXER, thereby a  
5 toner in Comparative Example 5A was obtained.

The diameter of the heating roller (HR) of the fixing unit used in the fixation by the toner in Comparative Example 5A is 40 mm, and the diameter of the pressing roller (PR) is 45 mm, and the fixing nip breadth  
10 at this time is 11.6 mm.

With these toners in Examples 1A to 5A and Comparative Examples 1A to 5A, amounts of release agent (wt.%) were computed, and initial relaxation modulus  $G(t=0.01)$  (Pa) at 120°C of each toner was measured by the  
15 above method. Further, initial relaxation modulus  $G(t=0.01)$  (Pa) at 180°C, and relaxation modulus in relaxation time of 0.1 sec  $G(t=0.1)$  (Pa) of each toner were measured, and the ratio showing relaxation velocity,  $[G(t=0.01)/G(t=0.1)]$  of each toner was computed.  
20 Further, fixing experiment was performed with each toner in Examples and Comparative Examples by the above fixing unit. The nip breadth (mm), temperature range in good region of offset (°C), and transparency HAZE value (%) were measured by the above methods, further, the winding of paper was  
25 observed by the above method. The results of the toners in

Examples 1A to 5A are shown in Table 1A, and the results of the toners in Comparative Examples 1A to 5A are shown in Table 2A.

Table 1A

	Example 1A	Example 2A	Example 3A	Example 4A	Example 5A
Amount of release agent (wt.%)	0	0.9	2.7	0.9	1.8
Initial relaxation modulus G (t=0.01) (Pa)	$2.12 \times 10^5$	$1.14 \times 10^5$	$4.66 \times 10^6$	$7.85 \times 10^5$	$2.50 \times 10^6$
Relaxation velocity G (t=0.01)/G (t=0.1)	61.1	32.5	55.6	23.4	35.8
Roller diameters of fixing unit (HR/PR) (mm)	30/35	20/25	30/35	30/35	40/45
Nip breadth (mm)	8.4	7.0	10.7	6.4	10.8
Winding	No	No	No	No	No
Good region of offset (°C)	130-195	130-195	145-200	145-190	140-200
Transparency (HAZE) (%)	8.7	13.2	12.4	9.2	14.2

Table 2A

	Comparative Example 1A	Comparative Example 2A	Comparative Example 3A	Comparative Example 4A	Comparative Example 5A
Amount of release agent (wt.%)	0.9	1.8	2.7	5.3	4.5
Initial relaxation modulus G (t=0.01) (Pa)	5.36x10 <sup>4</sup>	4.22x10 <sup>4</sup>	2.10x10 <sup>4</sup>	6.74x10 <sup>5</sup>	1.22x10 <sup>6</sup>
Relaxation velocity G (t=0.01)/G (t=0.1)	14.9	18.2	16.5	12.5	24.3
Roller diameters of fixing unit (HR/PR) (mm)	30/35	25/25	40/45	30/35	40/45
Nip breadth (mm)	8.4	7.1	8.8	10.7	11.6
Winding	Yes	Yes	Yes	No	No
Good region of offset (°C)	140-150	130-165	130-170	160-190	155-200
Transparency (HAZE) (%)	9.5	12.1	13.6	28.8	18.2

As is understood from the results in Table 1A,  
initial relaxation modulus  $G(t=0.01)$  (Pa) in relaxation  
time of 0.01 (sec), which was the starting time of  
measuring stress relaxation, of any of the toners in  
5 Examples 1A to 5A was  $1.0 \times 10^5$  (Pa) or more at 120°C, and  
the ratio (relaxation velocity)  $[G(t=0.01)/G(t=0.1)]$  at  
180°C was 23 or more.

All of the toners in Examples 1A to 5A were not  
accompanied by the winding of paper P around pressing  
10 roller 120. Further, all of the toners in Examples 1A to  
5A showed the breadth of the temperature range of good  
region of offset in which low temperature and hot offset  
traces did not occur of 45°C or more, thus these toners  
were confirmed to have a relatively broad temperature range.  
15 In addition, all of the toners in Examples 1A to 5A showed  
the HAZE value of 13.2(%) or less, thus these toners were  
confirmed to have good transparency.

Contrary to this, as is apparent from the results in  
Table 2A, initial relaxation modulus  $G(t=0.01)$  (Pa) in  
20 relaxation time of 0.01 (sec), the starting time of  
measuring stress relaxation, of any of the toners in  
Comparative Examples 1A to 3A was  $1.0 \times 10^5$  (Pa) or less at  
120°C. Further, it was confirmed that HAZE value of the  
toners in Comparative Examples 1A to 3A was 13.6(%) or less,  
25 which was a relatively small value and they showed good



transparency.

However, the ratio (relaxation velocity)  $[G(t=0.01)/G(t=0.1)]$  at 180°C of each toner in Comparative Examples 1A to 3A was 18.2 or less and a relatively small  
5 value. The toners in Comparative Examples 1A to 3A were accompanied by the winding of paper P around pressing roller 120. In addition, the toners in Comparative Examples 1A to 3A showed the breadth of the temperature range of good region of offset of 40°C or less, thus these  
10 toners were confirmed to have a relatively narrow temperature range.

Initial relaxation modulus  $G(t=0.01)$  (Pa) in relaxation time of 0.01 (sec), which was the starting time of measuring stress relaxation, at 120°C of the toners in  
15 Comparative Examples 4A and 5A was  $1.0 \times 10^5$  (Pa) or more. The toners in Comparative Examples 4A and 5A did not cause the winding of paper P around pressing roller 120.

However, the ratio (relaxation velocity)  $[G(t=0.01)/G(t=0.1)]$  at 180°C of each toner in Comparative  
20 Examples 4A and 5A was 24.3 or less and a relatively small value. In addition, the toners in Comparative Examples 4A and 5A showed the breadth of the temperature range of good region of offset of 45°C or less, thus these toners were confirmed to have a relatively narrow temperature range.

25 However, the HAZE values of the toners in Comparative

Examples 4A and 5A were both higher than 18.2(%) and relative great, thus they were not good in transparency.

### Second invention

5        Examples and Comparative Examples of the toners of the second invention are described below. The fixing unit described in Fig. 2 was used in the fixation by the toners in Examples and Comparative Examples.

      The manufacture of the resins for the toners of the  
10 second invention used in Examples and Comparative Examples is described below.

#### Resin 1B

      A mixture comprising 50 molar parts of neopentyl  
15 alcohol, 50 molar parts of ethylene glycol, 30 molar parts of 1,4-cyclohexanediol, 100 molar parts of dimethyl terephthalate, and 10 molar parts of phthalic anhydride was prepared.

      A two-liter four-necked flask was equipped with a  
20 reflux condenser, a distillation column, a water separator, a nitrogen gas introducing pipe, a thermometer and a stirrer according to an ordinary method, charged with 1,000 g of the above mixture and 1 g of an esterification condensation catalyst, and esterification reaction was  
25 carried out with bleeding water and methanol generated at

180°C from the distillation column. At the point when water and methanol stopped bleeding from the distillation column, the distillation column was detached from the two-liter four-necked flask and a vacuum pump was connected to the four-necked flask. The pressure in the system was lowered to 5 mmHg or less and the reaction system was stirred at a rotary speed of 150 rpm at 180°C. Free diol generated by the condensation reaction was discharged from the system, and the thus-obtained reaction product was taken as resin 1B. Resin 1B had a softening temperature (T<sub>m</sub>) of 114°C, a glass transition temperature (T<sub>g</sub>) of 63°C, and a weight average molecular weight (M<sub>w</sub>) of 18,000.

#### Resin 2B

A mixture comprising 70 molar parts of resin 1B, 15 molar parts of 1,4-butanediol, and 15 molar parts of dimethyl terephthalate was prepared.

A two-liter four-necked flask was equipped with a reflux condenser, a distillation column, a water separator, a nitrogen gas introducing pipe, a thermometer and a stirrer according to an ordinary method, charged with 1,000 g of the above mixture and 1 g of an esterification condensation catalyst, and esterification reaction was carried out with bleeding water and methanol generated at 200°C from the distillation column. At the point when

water and methanol stopped bleeding from the distillation column, the distillation column was detached from the two-liter four-necked flask and a vacuum pump was connected to the four-necked flask. The pressure in the system was  
5 lowered to 5 mmHg or less and the reaction system was stirred at a rotary speed of 150 rpm at 220°C. Free diol generated by the condensation reaction was discharged from the system, and the thus-obtained reaction product was taken as resin 2B. Resin 2B had a softening temperature  
10 (Tm) of 165°C, a glass transition temperature (Tg) of 64°C, and a weight average molecular weight (Mw) of 31,000.

#### Example 1B

To 100 parts by weight of resin 2B was added 20 parts  
15 by weight of pigment ~~Toner Magenta~~ TONER MAGENTA E02 (manufactured by Clariant Japan K.K.) as the colorant. The mixture was thoroughly blended by a ~~Henschel mixer~~ HENSCHEL MIXER and kneaded with a continuous system twin roll kneader (manufactured by MITSUI MINING COMPANY, LIMITED).  
20 The kneaded product was coarsely pulverized to a particle size of about 2 mm with a pulverizer (manufactured by HOSOKAWA MICRON CORPORATION), thereby a master batch was obtained.

To 30 parts by weight of the above-obtained master  
25 batch, 76 parts by weight of resin 1B, and 1 part by weight

of ~~Bontren~~ BONTRON E-84 (manufactured by Orient Chemical Industry Co., Ltd.) as CCA were added and thoroughly blended with a ~~Henschel-mixer~~ HENSCHEL MIXER, and melt-kneaded with a two-shaft extruder (manufactured by TOSHIBA MACHINE CO., LTD.), cooled to normal temperature (25°C),  
5 pulverized and classified with the above pulverizer and classifier (manufactured by HOSOKAWA MICRON CORPORATION), thereby mother particles having weight D50 of 8 µm were obtained. To 100 parts by weight of the mother particles,  
10 1.0 part by weight of silica RX200 (manufactured by Nippon Aerosil Co., Ltd.) was added and blended with a ~~Henschel-mixer~~ HENSCHEL MIXER, thereby a toner in Example 1B was obtained.

The diameter of the heating roller (HR) of the fixing  
15 unit used in the fixation by the toner in Example 1B is 30 mm, and the diameter of the pressing roller (PR) is 35 mm, and the fixing nip breadth at this time is 8.4 mm.

#### Example 2B

20 To 100 parts by weight of resin 2B was added 20 parts by weight of pigment ~~Toner-Magenta~~ TONER MAGENTA E02 (manufactured by Clariant Japan K.K.) as the colorant. The mixture was thoroughly blended by a ~~Henschel-mixer~~ HENSCHEL MIXER and kneaded with the above continuous system twin  
25 roll kneader. The kneaded product was coarsely pulverized

to a particle size of about 2 mm with the above pulverizer,  
to thereby obtain a master batch.

To 30 parts by weight of the above-obtained master  
batch, 76 parts by weight of resin 1B, 1 part by weight of  
5 ~~Bontren~~ BONTRON E-84 (manufactured by Orient Chemical  
Industry Co., Ltd.) as CCA, and 1 part by weight of  
~~earnauba-wax~~ CARNAUBA WAX (manufactured by NIPPON WAX  
CORPORATION) as the release agent were added and thoroughly  
blended with a ~~Henschel-mixer~~ HENSCHEL MIXER, and melt-  
10 kneaded with the above two-shaft extruder, cooled to normal  
temperature (25°C), pulverized and classified with the  
above pulverizer and classifier, thereby mother particles  
having weight D50 of 8 µm were obtained. To 100 parts by  
weight of the mother particles, 1.0 part by weight of  
15 silica RX200 (manufactured by Nippon Aerosil Co., Ltd.) was  
added and blended with a ~~Henschel-mixer~~ HENSCHEL MIXER,  
thereby a toner in Example 2B was obtained.

The diameter of the heating roller (HR) of the  
fixing unit used in the fixation by the toner in Example 2B  
20 is 20 mm, and the diameter of the pressing roller (PR) is  
25 mm, and the fixing nip breadth at this time is 7.0 mm.

### Example 3B

To 100 parts by weight of resin 2B was added 20 parts  
25 by weight of pigment ~~Toner-Magenta~~ TONER MAGENTA E02

(manufactured by Clariant Japan K.K.) as the colorant. The mixture was thoroughly blended by a ~~Henschel-mixer~~HENSCHEL MIXER and kneaded with the above continuous system twin roll kneader. The kneaded product was coarsely pulverized to a particle size of about 2 mm with the above pulverizer,  
5 to thereby obtain a master batch.

To 30 parts by weight of the above-obtained master batch, 76 parts by weight of resin 1B, 1 part by weight of ~~Bontren~~BONTRON E-84 (manufactured by Orient Chemical Industry Co., Ltd.) as CCA, and 3 parts by weight of ~~earnauba-wax~~CARNAUBA WAX (manufactured by NIPPON WAX CORPORATION) as the release agent were added and thoroughly blended with a ~~Henschel-mixer~~HENSCHEL MIXER, and melt-kneaded with the above two-shaft extruder, cooled to normal  
15 temperature (25°C), pulverized and classified with the above pulverizer and classifier, thereby mother particles having weight D50 of 8 µm were obtained. To 100 parts by weight of the mother particles, 1.0 part by weight of silica RX200 (manufactured by Nippon Aerosil Co., Ltd.) was  
20 added and blended with a ~~Henschel-mixer~~HENSCHEL MIXER, thereby a toner in Example 3B was obtained.

The diameter of the heating roller (HR) of the fixing unit used in the fixation by the toner in Example 3B is 30 mm, and the diameter of the pressing roller (PR) is  
25 35 mm, and the fixing nip breadth at this time is 10.7 mm.

#### Example 4B

To 100 parts by weight of resin 2B was added 10 parts by weight of pigment ~~Toner-Magenta~~TONER MAGENTA E02 (manufactured by Clariant Japan K.K.) as the colorant. The mixture was thoroughly blended by a ~~Henschel-mixer~~HENSCHEL MIXER and kneaded with the above continuous system twin roll kneader. The kneaded product was coarsely pulverized to a particle size of about 2 mm with the above pulverizer, to thereby obtain a master batch.

To 60 parts by weight of the above-obtained master batch, 46 parts by weight of resin 1B, 1 part by weight of ~~Bontren~~BONTRON E-84 (manufactured by Orient Chemical Industry Co., Ltd.) as CCA, and 1 part by weight of ~~earnauba-wax~~CARNAUBA WAX (manufactured by NIPPON WAX CORPORATION) as the release agent were added and thoroughly blended with a ~~Henschel-mixer~~HENSCHEL MIXER, and melt-kneaded with the above two-shaft extruder, cooled to normal temperature (25°C), pulverized and classified with the above pulverizer and classifier, thereby mother particles having weight D50 of 8  $\mu$ m were obtained. To 100 parts by weight of the mother particles, 1.0 part by weight of silica RX200 (manufactured by Nippon Aerosil Co., Ltd.) was added and blended with a ~~Henschel-mixer~~HENSCHEL MIXER, thereby a toner in Example 4B was obtained.



The diameter of the heating roller (HR) of the fixing unit used in the fixation by the toner in Example 4B is 30 mm, and the diameter of the pressing roller (PR) is 35 mm, and the fixing nip breadth at this time is 6.4 mm.

5

#### Example 5B

To 100 parts by weight of resin 2B was added 10 parts by weight of pigment ~~Toner Magenta~~TONER MAGENTA E02 (manufactured by Clariant Japan K.K.) as the colorant. The mixture was thoroughly blended by a ~~Henschel-mixer~~HENSCHEL MIXER and kneaded with the above continuous system twin roll kneader. The kneaded product was coarsely pulverized to a particle size of about 2 mm with the above pulverizer, to thereby obtain a master batch.

15 To 60 parts by weight of the above-obtained master batch, 46 parts by weight of resin 1B, 1 part by weight of ~~BONTRON~~BONTREN E-84 (manufactured by Orient Chemical Industry Co., Ltd.) as CCA, and 2 parts by weight of ~~earnauba-wax~~CARNAUBA WAX (manufactured by NIPPON WAX CORPORATION) as the release agent were added and thoroughly blended with a ~~Henschel-mixer~~HENSCHEL MIXER, and melt-kneaded with the above two-shaft extruder, cooled to normal temperature (25°C), pulverized and classified with the above pulverizer and classifier, thereby mother particles  
25 having weight D50 of 8 µm were obtained. To 100 parts by

weight of the mother particles, 1.0 part by weight of silica RX200 (manufactured by Nippon Aerosil Co., Ltd.) was added and blended with a ~~Henschel mixer~~HENSCHEL MIXER, thereby a toner in Example 5B was obtained.

5           The diameter of the heating roller (HR) of the fixing unit used in the fixation by the toner in Example 5B is 40 mm, and the diameter of the pressing roller (PR) is 45 mm, and the fixing nip breadth at this time is 10.8 mm.

10                           Comparative Example 1B

          To 100 parts by weight of a crosslinked polyester resin (manufactured by Sanyo Chemical Industries Co., Ltd.; softening temperature (Tm): 144°C, glass transition temperature (Tg): 60°C, weight average molecular weight  
15   (Mw): 29,000) was added 20 parts by weight of pigment ~~Toner~~TONER MAGENTA E02 (manufactured by Clariant Japan K.K.) as the colorant. The mixture was thoroughly blended by a ~~Henschel mixer~~HENSCHEL MIXER and kneaded with the above continuous system twin roll kneader. The kneaded  
20   product was coarsely pulverized to a particle size of about 2 mm with the above pulverizer, to thereby obtain a master batch.

          To 30 parts by weight of the above-obtained master batch, 76 parts by weight of a linear polyester resin  
25   (manufactured by Sanyo Chemical Industries Co., Ltd.;

softening temperature (Tm): 105°C, glass transition  
temperature (Tg): 68°C, weight average molecular weight  
(Mw): 11,500), 1 part by weight of ~~Bontren~~BONTRON E-84  
(manufactured by Orient Chemical Industry Co., Ltd.) as CCA,  
5 and 1 part by weight of ~~earnauba-wax~~CARNAUBA WAX  
(manufactured by NIPPON WAX CORPORATION) as the release  
agent were added and thoroughly blended with a ~~Henschel-~~  
~~mixer~~HENSCHEL MIXER, and melt-kneaded with the above two-  
shaft extruder, cooled to normal temperature (25°C),  
10 pulverized and classified with the above pulverizer and  
classifier, thereby mother particles having weight D50 of 8  
µm were obtained. To 100 parts by weight of the mother  
particles, 2.0 parts by weight of silica RX200  
(manufactured by Nippon Aerosil Co., Ltd.) was added and  
15 blended with a ~~Henschel-mixer~~HENSCHEL MIXER, thereby a  
toner in Comparative Example 1B was obtained.

The diameter of the heating roller (HR) of the  
fixing unit used in the fixation by the toner in  
Comparative Example 1B is 30 mm, and the diameter of the  
20 pressing roller (PR) is 35 mm, and the fixing nip breadth  
at this time is 8.4 mm.

#### Comparative Example 2B

To 100 parts by weight of a crosslinked polyester  
25 resin (manufactured by Sanyo Chemical Industries Co., Ltd.;

softening temperature (Tm): 144°C, glass transition  
temperature (Tg): 60°C, weight average molecular weight  
(Mw): 29,000) was added 20 parts by weight of pigment ~~Toner~~  
~~Magenta~~TONER MAGENTA E02 (manufactured by Clariant Japan  
5 K.K.) as the colorant. The mixture was thoroughly blended  
by a ~~Henschel mixer~~HENSCHEL MIXER and kneaded with the  
above continuous system twin roll kneader. The kneaded  
product was coarsely pulverized to a particle size of about  
2 mm with the above pulverizer, to thereby obtain a master  
10 batch.

To 30 parts by weight of the above-obtained master  
batch, 76 parts by weight of a linear polyester resin  
(manufactured by Sanyo Chemical Industries Co., Ltd.;  
softening temperature (Tm): 105°C, glass transition  
15 temperature (Tg): 68°C, weight average molecular weight  
(Mw): 11,500), 1 part by weight of ~~Bontren~~BONTRON E-84  
(manufactured by Orient Chemical Industry Co., Ltd.) as CCA,  
and 2 parts by weight of ~~earnauba wax~~CARNAUBA WAX  
(manufactured by NIPPON WAX CORPORATION) as the release  
20 agent were added and thoroughly blended with a ~~Henschel~~  
~~mixer~~HENSCHEL MIXER, and melt-kneaded with the above two-  
shaft extruder, cooled to normal temperature (25°C),  
pulverized and classified with the above pulverizer and  
classifier, thereby mother particles having weight D50 of 8  
25 µm were obtained. To 100 parts by weight of the mother

particles, 2.0 parts by weight of silica RX200  
(manufactured by Nippon Aerosil Co., Ltd.) was added and  
blended with a ~~Henschel mixer~~HENSCHEL MIXER, thereby a  
toner in Comparative Example 2B was obtained.

5           The diameter of the heating roller (HR) of the  
fixing unit used in the fixation by the toner in  
Comparative Example 2B is 20 mm, and the diameter of the  
pressing roller (PR) is also 25 mm, and the fixing nip  
breadth at this time is 7.1 mm.

10

#### Comparative Example 3B

To 100 parts by weight of a crosslinked polyester  
resin (manufactured by Sanyo Chemical Industries Co., Ltd.;  
softening temperature (T<sub>m</sub>): 144°C, glass transition  
15 temperature (T<sub>g</sub>): 60°C, weight average molecular weight  
(M<sub>w</sub>): 29,000) was added 20 parts by weight of pigment ~~Toner~~  
~~Magenta~~TONER MAGENTA E02 (manufactured by Clariant Japan  
K.K.) as the colorant. The mixture was thoroughly blended  
by a ~~Henschel mixer~~HENSCHEL MIXER and kneaded with the  
20 above continuous system twin roll kneader. The kneaded  
product was coarsely pulverized to a particle size of about  
2 mm with the above pulverizer, to thereby obtain a master  
batch.

To 40 parts by weight of the above-obtained master  
25 batch, 68 parts by weight of a linear polyester resin

(manufactured by Sanyo Chemical Industries Co., Ltd.; softening temperature (Tm): 105°C, glass transition temperature (Tg): 68°C, weight average molecular weight (Mw): 11,500), 1 part by weight of ~~Bontren~~BONTRON E-84  
5 (manufactured by Orient Chemical Industry Co., Ltd.) as CCA, and 3 parts by weight of ~~earnauba wax~~CARNAUBA WAX (manufactured by NIPPON WAX CORPORATION) as the release agent were added and thoroughly blended with a ~~Hensehel-mixer~~HENSCHEL MIXER, and melt-kneaded with the above two-  
10 shaft extruder, cooled to normal temperature (25°C), pulverized and classified with the above pulverizer and classifier, thereby mother particles having weight D50 of 8 µm were obtained. To 100 parts by weight of the mother particles, 2.0 parts by weight of silica RX200  
15 (manufactured by Nippon Aerosil Co., Ltd.) was added and blended with a ~~Hensehel-mixer~~HENSCHEL MIXER, thereby a toner in Comparative Example 3B was obtained.

The diameter of the heating roller (HR) of the fixing unit used in the fixation by the toner in  
20 Comparative Example 3B is 30 mm, and the diameter of the pressing roller (PR) is 35 mm, and the fixing nip breadth at this time is 8.8 mm.

#### Comparative Example 4B

25 To 100 parts by weight of a crosslinked polyester

resin (manufactured by Sanyo Chemical Industries Co., Ltd.; softening temperature (Tm): 144°C, glass transition temperature (Tg): 60°C, weight average molecular weight (Mw): 29,000) was added 10 parts by weight of pigment ~~Toner~~  
5 ~~Magenta~~TONER MAGENTA E02 (manufactured by Clariant Japan K.K.) as the colorant. The mixture was thoroughly blended by a ~~Henschel-mixer~~HENSCHEL MIXER and kneaded with the above continuous system twin roll kneader. The kneaded product was coarsely pulverized to a particle size of about  
10 2 mm with the above pulverizer, to thereby obtain a master batch.

To 60 parts by weight of the above-obtained master batch, 46 parts by weight of a linear polyester resin (manufactured by Sanyo Chemical Industries Co., Ltd.;  
15 softening temperature (Tm): 105°C, glass transition temperature (Tg): 68°C, weight average molecular weight (Mw): 11,500), 1 part by weight of ~~Bontren~~BONTRON E-84 (manufactured by Orient Chemical Industry Co., Ltd.) as CCA, and 6 parts by weight of ~~earnauba-wax~~CARNAUBA WAX  
20 (manufactured by NIPPON WAX CORPORATION) as the release agent were added and thoroughly blended with a ~~Henschel-mixer~~HENSCHEL MIXER, and melt-kneaded with the above two-shaft extruder, cooled to normal temperature (25°C), pulverized and classified with the above pulverizer and  
25 classifier, thereby mother particles having weight D50 of 8

μm were obtained. To 100 parts by weight of the mother particles, 2.0 parts by weight of silica RX200 (manufactured by Nippon Aerosil Co., Ltd.) was added and blended with a ~~Henschel-mixer~~HENSCHEL MIXER, thereby a  
5 toner in Comparative Example 4B was obtained.

The diameter of the heating roller (HR) of the fixing unit used in the fixation by the toner in Comparative Example 4B is 25 mm, and the diameter of the pressing roller (PR) is also 25 mm, and the fixing nip  
10 breadth at this time is 10.7 mm.

#### Comparative Example 5B

To 100 parts by weight of a crosslinked polyester resin (manufactured by Sanyo Chemical Industries Co., Ltd.;  
15 softening temperature (T<sub>m</sub>): 144°C, glass transition temperature (T<sub>g</sub>): 60°C, weight average molecular weight (M<sub>w</sub>): 29,000) was added 20 parts by weight of pigment ~~Toner~~MagentaTONER MAGENTA E02 (manufactured by Clariant Japan K.K.) as the colorant. The mixture was thoroughly blended  
20 by a ~~Henschel-mixer~~HENSCHEL MIXER and kneaded with the above continuous system twin roll kneader. The kneaded product was coarsely pulverized to a particle size of about 2 mm with the above pulverizer, to thereby obtain a master batch.

25 To 30 parts by weight of the above-obtained master



batch, 76 parts by weight of a crosslinked polyester resin  
(manufactured by Sanyo Chemical Industries Co., Ltd.;  
softening temperature (Tm): 144°C, glass transition  
temperature (Tg): 60°C, weight average molecular weight  
5 (Mw): 29,000), 1 part by weight of ~~Bontren~~BONTRON E-84  
(manufactured by Orient Chemical Industry Co., Ltd.) as CCA,  
and 5 parts by weight of ~~earnauba-wax~~CARNAUBA WAX  
(manufactured by NIPPON WAX CORPORATION) as the release  
agent were added and thoroughly blended with a ~~Henschel-~~  
10 ~~mixer~~HENSCHEL MIXER, and melt-kneaded with the above two-  
shaft extruder, cooled to normal temperature (25°C),  
pulverized and classified with the above pulverizer and  
classifier, thereby mother particles having weight D50 of 8  
µm were obtained. To 100 parts by weight of the mother  
15 particles, 2.0 parts by weight of silica RX200  
(manufactured by Nippon Aerosil Co., Ltd.) was added and  
blended with a ~~Henschel-mixer~~HENSCHEL MIXER, thereby a  
toner in Comparative Example 5B was obtained.

The diameter of the heating roller (HR) of the  
20 fixing unit used in the fixation by the toner in  
Comparative Example 5B is 40 mm, and the diameter of the  
pressing roller (PR) is 45 mm, and the fixing nip breadth  
at this time is 11.6 mm.

With these toners in Examples 1B to 5B and  
25 Comparative Examples 1B to 5B, amounts of release agent

(wt.%) were computed, and initial relaxation modulus  $G$  ( $t=0.01$ ) (Pa) at 120°C and 180°C of each toner were measured by the above method. Further, fixing experiment was performed with each toner in Examples and Comparative Examples by the above fixing unit. Temperature range in good region of offset (°C), and transparency HAZE value (%) were measured by the above methods, further, the winding of paper was observed by the above method. The results of the toners in Examples 1B to 5B are shown in Table 1B, and the results of the toners in Comparative Examples 1B to 5B are shown in Table 2B.

Table 1B

	Example 1B	Example 2B	Example 3B	Example 4B	Example 5B
Amount of release agent (wt.%)	0	0.9	2.7	0.9	1.8
Initial relaxation modulus G (t=0.01) (Pa) at 120°C	2.57x10 <sup>5</sup>	6.58x10 <sup>5</sup>	1.13x10 <sup>6</sup>	8.65x10 <sup>5</sup>	2.41x10 <sup>6</sup>
Initial relaxation modulus G (t=0.01) (Pa) at 180°C	1.50x10 <sup>4</sup>	1.23x10 <sup>4</sup>	2.35x10 <sup>4</sup>	8.54x10 <sup>4</sup>	9.54x10 <sup>4</sup>
Roller diameters of fixing unit (HR/PR) (mm)	30/35	20/25	30/35	30/35	40/45
Nip breadth (mm)	8.4	7.0	10.7	6.4	10.8
Winding	No	No	No	No	No
Good region of offset (°C)	130-195	130-195	145-200	145-190	140-200
Transparency (HAZE) (%)	8.7	12.1	14.3	9.8	10.2

Table 2B

	Comparative Example 1B	Comparative Example 2B	Comparative Example 3B	Comparative Example 4B	Comparative Example 5B
Amount of release agent (wt. %)	0.9	1.8	2.7	5.3	4.5
Initial relaxation modulus G (t=0.01) (Pa) at 120°C	8.56x10 <sup>4</sup>	2.58x10 <sup>4</sup>	1.21x10 <sup>4</sup>	9.41x10 <sup>5</sup>	5.44x10 <sup>5</sup>
Initial relaxation modulus G (t=0.01) (Pa) at 180°C	1.24x10 <sup>3</sup>	9.74x10 <sup>3</sup>	2.55x10 <sup>3</sup>	3.22x10 <sup>4</sup>	2.31x10 <sup>4</sup>
Roller diameters of fixing unit (HR/PR) (mm)	30/35	20/25	30/35	25/25	40/45
Nip breadth (mm)	8.4	7.1	8.8	10.7	11.6
Winding	Yes	Yes	Yes	Yes	No
Good region of offset (°C)	140-150	130-165	130-170	130-195	140-200
Transparency (HAZE) (%)	9.4	10.8	11.5	31.5	24.6

As is understood from the results in Table 1B, the amount of release agent of each toner in Examples 1B to 5B was 3 wt.% or less, and initial relaxation modulus  $G$  ( $t=0.01$ ) (Pa) in relaxation time of 0.01 (sec), which was  
5 the starting time of measuring stress relaxation, of all of the toners in Examples 1B to 5B was  $1.0 \times 10^5$  (Pa) or more at  $120^\circ\text{C}$ , and  $1.0 \times 10^4$  (Pa) or more at  $180^\circ\text{C}$ .

All of the toners in Examples 1B to 5B were not accompanied by the winding of paper. Further, all of the  
10 toners in Examples 1B to 5B showed the breadth of the temperature range of good region of offset in which low temperature and hot offset traces did not occur of  $45^\circ\text{C}$  or more, thus these toners were confirmed to have a relatively broad temperature range. In addition, all of the toners in  
15 Examples 1B to 5B showed the HAZE value of 14.3(%) or less, thus these toners were confirmed to have good transparency.

Contrary to this, as is apparent from the results in Table 2B, the amount of release agent of each toner in Comparative Examples 1B to 3B was 3 wt.% or less, initial  
20 relaxation modulus  $G$  ( $t=0.01$ ) (Pa) was smaller than  $1.0 \times 10^5$  (Pa) at  $120^\circ\text{C}$  in any of the toners in Comparative Examples 1B to 3B, and smaller than  $1.0 \times 10^4$  (Pa) at  $180^\circ\text{C}$ . Further, it was confirmed that HAZE value of the toners in Comparative Examples 1B to 3B was 11.5(%) or less, which  
25 was a relatively small value and they showed good

transparency.

However, the toners in Comparative Examples 1B to 3B were accompanied by the winding of paper. In addition, the toners in Comparative Examples 1B to 3B showed the breadth  
5 of the temperature range of good region of offset of 40°C or less, thus these toners were confirmed to have a relatively narrow temperature range.

The amount of release agent of each toner in Comparative Examples 4B and 5B was 3 wt.% or more, initial  
10 relaxation modulus  $G(t=0.01)$  (Pa) was  $1.0 \times 10^5$  (Pa) or more at 120°C and  $1.0 \times 10^4$  (Pa) or more at 180°C in the toners in Comparative Examples 4B and 5B. Further, the toners in Comparative Examples 4B and 5B did not bring about winding of paper, and the breadth of the temperature range of good  
15 region of offset of these toners in Comparative Examples 4B and 5B was 60°C or more, thus these toners were confirmed to have a relatively broad temperature range.

However, HAZE value of the toners in Comparative Examples 4B and 5B was 24.6(%) or more, thus good  
20 transparency cannot be obtained from these toners.

In the toner of the first invention having such a constitution, an unfixed toner on a recording medium is fixed by heating by the main heating member of the oil-less  
25 fixing unit from the backside of the toner. Since the

fixing nip part of the oil-less fixing unit takes the configuration protruding toward the side of main heating member, the recording medium is discharged from the fixing nip outlet along by the protruding configuration of the  
5 fixing nip. Therefore, the fixed toner on the recording medium tries to move along by the pressing member. And the temperature of the fixed toner on the recording medium discharged from the fixing nip outlet comes to lower.

However, in stress relaxation measurement, the toner  
10 of the first invention has initial relaxation modulus  $G(t=0.01)$  (Pa) in relaxation time of 0.01 (sec), which is the starting time of measuring stress relaxation, at 120°C of: initial relaxation modulus  $G(t=0.01)$  [Pa]  $\geq 1.0 \times 10^5$  [Pa], thus the toner melted in the fixing nip is brought to  
15 have relatively sufficient elasticity after the fixing nip outlet. Accordingly, the toner does not adhere to the pressing member after the fixing nip outlet due to the elasticity, as a result, the winding of the recording medium round the pressing member after heating fixation on  
20 the backside can be prevented.

In addition, the winding of a recording medium round the pressing member can be prevented, so that it is not necessary to forcibly peel a recording medium from the pressing member. Accordingly, when a recording medium  
25 peels off the pressing member after the fixing nip outlet,

hot offset by the reluctance of separation of the toner can also be prevented.

On the other hand, in the heat-fixing unit in which the toner of the first invention is used, heating fixation is performed from the backside of the fixing surface of the toner via a recording medium, so that the toner cannot be heated directly. However, the ratio of the initial relaxation modulus  $G(t=0.01)$  (Pa) to the relaxation modulus  $G(t=0.1)$  (Pa) in relaxation time of 0.1 sec at 180°C of the toner of the first invention,  $[G(t=0.01)/G(t=0.1)]$ , is set at 20 or more. The ratio represents the relaxation velocity of the toner, and the toner melts almost completely in fixing nip, since the relaxation velocity of the toner increases. Accordingly, good fixing property that does not bring about hot offset can be secured.

Thus according to the toner of the first invention, good fixing characteristics can be secured even with an oil-less fixing unit, and the winding of the recording medium round the pressing member in backside heating fixation can also be prevented by organically combining the fixing nip configuration protruding toward the side of main heating member, performing heating fixation from the backside of the fixing surface of the toner, setting initial relaxation modulus of the toner at 120°C,  $G$



( $t=0.01$ ) [Pa], at  $1.0 \times 10^5$  [Pa] or higher, and setting the ratio of the initial relaxation modulus  $G$  ( $t=0.01$ ) (Pa) to the relaxation modulus  $G$  ( $t=0.1$ ) (Pa) in relaxation time of 0.1 sec at 180°C of the toner,  $[G(t=0.01)/G(t=0.1)]$ , at  
5 20 or more.

In particular, according to the toner of the first invention, not only hot offset of the toner and winding of a recording medium can be effectively prevented, but also a good transparent image can be obtained by setting the  
10 content of a release agent at 3 wt.% or less to thereby reduce the content, or even when a release agent is not used.

Although the toner of the first invention is in contact with a pressing member, the toner is fixed on a  
15 recording medium without adhering to the pressing member (without causing offset) by the increase of elasticity and viscosity. Since the toner of the first invention is excellent in offset resistance at high temperature, it is not necessary to coat a release agent, e.g., silicone oil,  
20 on the surface of the pressing member.

In the toner of the second invention having such a constitution, an unfixed toner on a recording medium is fixed by heating by the main heating member of the oil-less fixing unit from the backside of the toner. Since the  
25 fixing nip part of the oil-less fixing unit takes the

configuration protruding toward the side of pressing, the recording medium is discharged from the fixing nip outlet along by the protruding configuration of the fixing nip. Therefore, the fixed toner on the recording medium tries to  
5 move along by the heating member. And the temperature of the fixed toner on the recording medium discharged from the fixing nip outlet comes to lower.

However, in stress relaxation measurement, the toner of the second invention has initial relaxation modulus  $G$   
10  $(t=0.01)$  (Pa) in relaxation time of 0.01 (sec), which is the starting time of measuring stress relaxation, at 120°C of: initial relaxation modulus  $G(t=0.01)$  [Pa]  $\geq 1.0 \times 10^5$  [Pa], thus the toner melted in the fixing nip is brought to have relatively sufficient elasticity after the fixing nip  
15 outlet. Accordingly, the toner does not adhere to the pressing member after the fixing nip outlet due to the elasticity, as a result, the winding of the recording medium round the pressing member after heating fixation on the backside can be prevented.

20 In addition, the winding of a recording medium round the pressing member can be prevented, so that it is not necessary to forcibly peel a recording medium from the pressing member. Accordingly, when a recording medium peels off the pressing member after the fixing nip outlet,  
25 hot offset by the reluctance of separation of the toner can

also be prevented.

On the other hand, if the elasticity of the toner is too small when the toner is heated before the outlet of fixing nip, the toner hardens with difficulty even if cooled after the nip outlet. Accordingly, there is the possibility that hot offset due to the reluctance of separation of the toner occurs. By setting initial relaxation modulus  $G(t=0.01)$  [Pa] at  $180^{\circ}\text{C}$  at  $1.0 \times 10^4$  [Pa] or higher, the elasticity of the toner before fixing nip outlet is restricted so as not to lower than a certain degree. By this contrivance, the toner appropriately hardens and hot offset due to the reluctance of separation of the toner does not occur when cooled after the nip outlet.

Thus according to the toner of the second invention, good fixing characteristics can be secured even with an oil-less fixing unit, and the winding of the recording medium round the pressing member in backside heating fixation can also be prevented by organically combining the fixing nip configuration protruding toward the side of pressing member, performing heating fixation from the backside of the fixing surface of the toner, setting initial relaxation modulus of the toner at  $120^{\circ}\text{C}$ ,  $G(t=0.01)$  [Pa], at  $1.0 \times 10^5$  [Pa] or higher, and setting initial relaxation modulus of the toner at  $180^{\circ}\text{C}$ ,  $G$

( $t=0.01$ ) [Pa], at  $1.0 \times 10^4$  [Pa] or higher.

In particular, according to the toner of the second invention, not only hot offset of the toner and winding of a recording medium can be effectively prevented, but also a good transparent image can be obtained by setting the content of a release agent at 3 wt.% or less to thereby reduce the content, or even when a release agent is not used.

Although the toner of the second invention is in contact with a pressing member, the toner is fixed on a recording medium without adhering to the pressing member (without causing offset) by the increase of elasticity and viscosity. Since the toner of the second invention is excellent in offset resistance at high temperature, it is not necessary to coat a release agent, e.g., silicone oil, on the surface of the pressing member.

While the present invention has been described in detail and with reference to specific embodiments thereof, it will be apparent to one skilled in the art that various changes and modifications can be made therein without departing the spirit and scope thereof.

The present application is based on Japanese Patent Application No. 2003-53762 and 2003-53763, both thereof filed on February 28, 2003, and the contents thereof are incorporated herein by reference.



WHAT IS CLAIMED IS:

1. A toner for use in an image-forming apparatus  
5 equipped with an oil-less fixing unit comprising a main  
heating member and a pressing member, the main heating  
member gets in contact with the back of an unfixed toner on  
a recording medium and fixes the unfixed toner at a nip  
part of the main heating member and the pressing member,  
10 the main heating member and the pressing member define a  
boundary surface thereof, and the surface takes a  
configuration protruding toward the side of the main  
heating member,

wherein the toner has a initial relaxation modulus  $G$   
15 ( $t=0.01$ ) (Pa) at 120°C, in relaxation time of 0.01 (sec),  
of  $G$  ( $t=0.01$ ) [Pa]  $\geq 1.0 \times 10^5$  [Pa],

wherein the toner has a ratio of  $G$  ( $t=0.01$ ) (Pa) to  
 $G$  ( $t=0.1$ ) (Pa) at 180°C, in relaxation time of 0.1 sec, of  
[ $G$  ( $t=0.01$ )/ $G$  ( $t=0.1$ )]  $\geq 20$ .

20

2. The toner according to claim 1, wherein the  
toner contains a release agent in an amount of 3 wt.% or  
less.

25

3. A toner for use in an image-forming apparatus equipped with an oil-less fixing unit comprising a main heating member and a pressing member, the main heating member gets in contact with the back of an unfixed toner on a recording medium and fixes the unfixed toner at a nip part of the main heating member and the pressing member, the main heating member and the pressing member define a boundary surface thereof, and the surface takes a configuration protruding toward the side of the main pressing member,

wherein the toner has a initial relaxation modulus  $G(t=0.01)$  (Pa) at 120°C, in relaxation time of 0.01 (sec), of  $G(t=0.01)$  [Pa]  $\geq 1.0 \times 10^5$  [Pa],

wherein the toner has a initial relaxation modulus  $G(t=0.01)$  (Pa) at 180°C, in relaxation time of 0.01 (sec), of  $G(t=0.01)$  [Pa]  $\geq 1.0 \times 10^4$  [Pa].

4. The toner according to claim 3, wherein the toner contains a release agent in an amount of 3 wt.% or less.

#### ABSTRACT OF THE DISCLOSURE

The present invention provides a toner capable of effectively controlling hot offset of a toner in fixing characteristics, while effectively preventing the winding  
5 of a recording medium round a fixing member.